12X 352 D Page 1 of 4 June 2014

HOLLAND HOUSE • QUEENS ROAD • BARNET • EN5 4DJ • ENGLAND • TEL: +44 (0)20 8441 2024 • FAX: +44 (0)20 8449 0810 email: info@mbh.co.uk web: www.mbh.co.uk

CERTIFICATE OF ANALYSIS

12X 352 (batch D)

Certified Reference Material Information

Type: LOW-ALLOY STEEL (WROUGHT)

Form and Size: Disc ~40mm diameter

Manufactured by: Polycast Ltd

Certified and Supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

Element	С	Si	S	Р	Mn	Ni	Cr	Мо
Value ¹	0.298	0.338	0.125	0.066	0.627	0.334	0.423	0.257
Uncertainty ²	0.004	0.006	0.003	0.002	0.006	0.003	0.002	0.004

Element	Cu	Со	Sn	Al	W	Ti	V	As
Value ¹	0.144	0.0504	0.105	0.146	0.223	0.285	0.0584	0.0095
Uncertainty ²	0.004	0.0009	0.002	0.004	0.004	0.006	0.0012	0.0007

Definitions

- The assigned values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:		on 11th June 2014
MBH ANALYTICAL LIMITED_		
	C Eveleigh	

Method of Preparation

This reference material was produced from commercial-purity metals and master alloys. The discs are the product of one melt, cast into 70mm diameter billets and hot worked into bars of ~42mm diameter.

Sampling

Milled samples for chemical analysis were taken from several positions within the batch. In addition, at least 10% of all discs were selected for homogeneity checking.

Homogeneity

The discs were checked for lateral and batch uniformity using an optical emission spectrometer.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Steels are generally prepared by grinding. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer. Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible interelement effects.

Analytical Data

Percentage element by weight								
Sample	С	Si	S	Р	Mn	Ni	Cr	Мо
1	0.290	0.325	0.123	0.0630	0.618	0.327	0.420	0.245
2	0.293	0.327	0.123	0.0636	0.621	0.328	0.421	0.248
3	0.294	0.328	0.123	0.0651	0.625	0.330	0.421	0.251
4	0.294	0.329	0.123	0.0652	0.626	0.331	0.421	0.252
5	0.295	0.330	0.124	0.0655	0.627	0.333	0.421	0.252
6	0.296	0.333	0.124	0.0656	0.628	0.334	0.423	0.253
7	0.297	0.334	0.124	0.0658	0.630	0.335	0.424	0.254
8	0.300	0.339	0.124	0.0677	0.632	0.335	0.425	0.256
9	0.301	0.342	0.126	0.0685	0.637	0.336	0.425	0.261
10	0.302	0.344	0.127	0.0687		0.336	0.426	0.261
11	0.306	0.347	0.127	0.0692		0.337		0.261
12	0.306	0.349	0.128			0.342		0.263
13		0.349	0.128			0.342		0.264
14		0.351	0.128					0.265
15								0.267
Mean	0.298	0.338	0.125	0.0662	0.627	0.334	0.423	0.257
Std Dev	0.005	0.009	0.002	0.0021	0.006	0.005	0.002	0.007
C _(95%)	0.003	0.005	0.001	0.0014	0.004	0.003	0.002	0.004
Sample	Cu	Co	Sn	Al	W	Ti	٧	As
1	0.135	0.0484	0.1022	0.139	0.212	0.277	0.0561	0.0078
2	0.135	0.0489	0.1027	0.140	0.215	0.277	0.0563	0.0083
3	0.136	0.0490	0.1037	0.141	0.216	0.280	0.0567	0.0084
4	0.137	0.0496	0.1039	0.141	0.217	0.281	0.0580	0.0089
5	0.139	0.0496	0.1047	0.143	0.219	0.284	0.0580	0.0090
6	0.140	0.0502	0.1051	0.145	0.221	0.285	0.0582	0.0090
7	0.140	0.0505	0.1060	0.146	0.222	0.285	0.0583	0.0091
8	0.141	0.0510	0.1061	0.147	0.224	0.289	0.0585	0.0100
9	0.147	0.0511	0.1063	0.148	0.225	0.290	0.0586	0.0105
10	0.149	0.0518	0.1064	0.148	0.226	0.291	0.0591	0.0105
11	0.150	0.0519	0.1072	0.149	0.231	0.291	0.0592	0.0106
12	0.150	0.0528	0.1089	0.149	0.235		0.0593	0.0113
13	0.151			0.150	0.235		0.0596	
14	0.152			0.150			0.0598	
15	0.155			0.151			0.0608	
Mean	0.144	0.0504	0.1053	0.146	0.223	0.285	0.0584	0.0095
Std Dev	0.007	0.0014	0.0019	0.004	0.007	0.005	0.0013	0.0011
C _(95%)	0.004	0.0009	0.0012	0.002	0.004	0.004	0.0007	0.0007

Note: $C_{(95\%)}$ is the 95% half-width confidence interval derived from the equation:

 $C_{(95\%)} = (t \times SD)/\sqrt{n}$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Exova Ltd
Sheffield Assay Office
Metals Technology (Testing) Ltd
Universal Scientific Laboratory Pty Ltd
Laboratory Testing, Inc
Shanghai Jinyi Test Tech Co
Shandong Metallurgical & Science Research
Bureau Veritas CPS Pvt
Raghavendra SpectroMet Laboratory
Genitest Inc
Tec-Eurolab
Instytut Metalurgii Zelaza
London & Scandinavian Met Co
Coleshill Laboratories Ltd
Lithea sro
Mineral & Metallurgical Laboratories

Middlesbrough, England Sheffield, England Sheffield, England Milperra, NSW, Australia Hatfield, PA, USA Shanghai, China Jinan, Shandong, China Chennai, India Bangalore, India Montreal, Canada Campogalliano, Italy Gliwice, Poland Rotherham, England Birmingham, England Brno, Czech Republic Bangalore, India

UKAS accreditation 0239
UKAS accreditation 0012
UKAS accreditation 0963
NATA accreditation 492
A2LA accreditation 0117
CNAS accreditation L0041
CNAS accreditation 1061
NABL accreditation 0025
NABL accreditation T371
PRI accreditation 123077
ACCREDIA accreditation 52
PCA accreditation AB554

Note: to achieve the above accreditation (UKAS, NATA, etc), test houses are required to demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT		R	ESULT No. & METI	HOD
	ICP-AES	FAAS		OTHER
Carbon	-	-	all	combustion (IR or volumetric detection)
Silicon	1, 2, 6-8, 13, 14	-	3, 4, 11, 12	gravimetric (perchloric acid)
			5, 9, 10	photometric (molybdenum blue)
Sulfur	1	-	2-14	combustion (IR or volumetric detection)
Phosphorus	1, 2, 4-8, 10, 11	-	3, 9	photometric (molybdenum blue)
Manganese	2, 3, 5, 7-9	1	4	volumetric (arsenite)
			6	photometric (periodate)
Nickel	1, 2, 5, 6, 8-11	12, 13	3, 4	photometric (dimethyl glyoxime)
			7	gravimetric (dimethyl glyoxime)
Chromium	3-7, 9, 10	1	2, 8	volumetric (FAS)
Molybdenum	1-3, 5-7, 10-13, 15	9, 14	4, 8	photometric (thiocyanate)
Copper	1-6, 10, 12-14	7, 8, 11	9	photometric (BCO)
			15	volumetric (thiosulfate)
Cobalt	1-4, 7, 8, 10-12	6, 9	5	volumetric (iodine)
Tin	1-4, 7-12	5, 6		
Aluminium	3-5, 7-9, 11-14	2, 6, 15	1, 10	photometric (chrome azurol S)
Tungsten	1-3, 7-13	5	4	photometric (thiocyanate)
			6	ICP-MS
Titanium	1-3, 5, 7-10	4, 11	6	photometric (DAP)
Vanadium	1-3, 6, 7, 9-11, 13, 14	4, 8, 12	5, 15	volumetric (fFAS)
Arsenic	1-7, 9-12	8		

Notes

This Certified Reference Material has been produced and certified, wherever possible, in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2000 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

This certification is applicable to the whole of the disc. However, in accordance with normal practice for emission spectrometry, it is appropriate to avoid usage of the centre of the disc, ~8 mm diameter.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in June 2034, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.