

CERTIFICATE OF ANALYSIS

13X 19003 (batch C)

Certified Reference Material Information

Type: AUSTENITIC STAINLESS STEEL (WROUGHT)

Form and Size: Disc ~40mm diameter

Manufactured by: Polycast Ltd

Certified and Supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

Element	C	Si	S	P	Mn	Ni	Cr
Value ¹	0.047	0.497	0.046	0.0382	1.138	12.46	18.99
Uncertainty ²	0.002	0.008	0.002	0.0014	0.011	0.05	0.11

Element	Mo	Cu	Co	Nb	Ta	V	N
Value ¹	2.50	0.171	0.105	0.120	(0.005)	0.0486	0.077
Uncertainty ²	0.02	0.003	0.003	0.002	-	0.0014	0.002

Definitions

- ¹ The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- ² The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:

MBH ANALYTICAL LIMITED _____ on 27th April 2016

L Maxim



Method of Preparation

This reference material was produced from commercial-purity metals and master alloys. The discs are the product of one melt, cast into 70mm diameter billets and hot worked into bars of ~42mm diameter.

Sampling

Samples for chemical analysis were taken from various positions throughout the batch. At least 10% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

Samples representative of the batch were checked for uniformity using an optical emission spectrometer. Multiple measurements were taken from each surface under test.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Steels are generally prepared by finishing, grinding, turning or milling. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

For optical emission spectroscopy, a minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

Sample	C	Si	S	P	Mn	Ni	Cr
1	0.0427	0.478	0.0412	0.0350	1.110	12.32	18.73
2	0.0429	0.484	0.0431	0.0355	1.112	12.35	18.76
3	0.0436	0.486	0.0448	0.0362	1.125	12.37	18.79
4	0.0440	0.490	0.0451	0.0364	1.132	12.39	18.85
5	0.0444	0.494	0.0451	0.0380	1.138	12.42	19.01
6	0.0452	0.500	0.0453	0.0384	1.142	12.45	19.03
7	0.0474	0.500	0.0459	0.0387	1.143	12.46	19.04
8	0.0476	0.500	0.0482	0.0393	1.146	12.52	19.05
9	0.0498	0.503	0.0493	0.0399	1.149	12.52	19.13
10	0.0500	0.505	0.0493	0.0399	1.151	12.53	19.14
11	0.0501	0.506	0.0498	0.0403	1.152	12.53	19.15
12	0.0508	0.512		0.0410	1.152	12.55	19.20
13	0.0521					12.57	
Mean	0.0470	0.497	0.0461	0.0382	1.138	12.46	18.99
Std Dev	0.0033	0.010	0.0028	0.0020	0.015	0.08	0.17
C (95%)	0.0020	0.006	0.0019	0.0013	0.009	0.05	0.10

Sample	Mo	Cu	Co	Nb	Ta	V	N
1	2.446	0.165	0.1002	0.1150	0.0042	0.0444	0.0750
2	2.452	0.169	0.1008	0.1155	0.0042	0.0445	0.0759
3	2.474	0.169	0.1012	0.1163	0.0046	0.0459	0.0777
4	2.476	0.170	0.1015	0.1168	0.0046	0.0485	0.0782
5	2.480	0.171	0.1022	0.1190	0.0049	0.0485	0.0784
6	2.486	0.172	0.1023	0.1190	0.0052	0.0488	0.0793
7	2.488	0.172	0.1030	0.1192		0.0492	
8	2.500	0.176	0.1059	0.1200		0.0499	
9	2.512	0.179	0.1090	0.1210		0.0501	
10	2.520		0.1093	0.1210		0.0501	
11	2.522		0.1099	0.1240		0.0504	
12	2.533		0.1100	0.1240		0.0507	
13	2.534		0.1102	0.1243		0.0509	
14	2.546						
Mean	2.498	0.171	0.1050	0.1196	0.0046	0.0486	0.0774
Std Dev	0.031	0.004	0.0041	0.0032	0.0004	0.0023	0.0016
C (95%)	0.018	0.003	0.0025	0.0019	0.0004	0.0014	0.0017

Note: $C_{(95\%)}$ is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Exova Ltd	Middlesbrough, UK	UKAS accreditation	0239
Sheffield Analytical Services	Sheffield, UK	UKAS accreditation	0012
Metals Technology (Testing) Ltd.	Sheffield, UK	UKAS accreditation	0963
Universal Scientific Laboratory Pty Ltd	Milperra, Australia	NATA accreditation	0492
Shanghai JinYi Test Technology Co. Ltd	Shanghai, China	CNAL accreditation	0783
Shandong Metallurgical & Science Research	Jinan, Shandong, China	CNAS accreditation	1461
Bureau Veritas CPS pvt Ltd.	Chennai, India	NABL accreditation	0025
TCR Engineering Services pvt. Ltd.	Mumbai, India	NABL accreditation	0367
Raghavendra Spectro Metallurgical Laboratory	Bangalore, India	NABL accreditation	0371
Instytut Metalurgii Zelaza	Gliwice, Poland	PCA accreditation	AB554
TEC Eurolab SRL	Modena, Italy	ACCREDIA accreditation	52
Mineral and Metallurgical Laboratories	Bangalore, India		
AMG Superalloys UK Ltd	Rotherham, UK		
Analyticka Laborator Lithea sro	Brno, Czech Republic		
Coleshill Laboratories Ltd	Coleshill, UK		

Note: to achieve the above-noted accreditation (eg UKAS, NATA, etc), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT	RESULT No. & METHOD		
	ICP-AES	FAAS	OTHER
Carbon	-	-	1-13 combustion (infra-red detection)
Silicon	4-7, 9-10	-	1-3 photometric (molybdenum blue)
Sulfur	4, 8	-	8, 11, 12 gravimetric (perchloric acid)
Phosphorus	1, 5, 7, 9, 10, 12	-	1-3, 5-7, 9-11 combustion (infra-red detection)
Manganese	2, 3, 7, 9, 10, 12	1, 5	2, 3, 11 volumetric (alkalimetric)
Nickel	2, 5, 6, 10, 12	9	4, 6, 8 photometric (molybdenum blue)
Chromium	3, 7, 8, 11, 12	-	4, 6 photometric (periodate)
Molybdenum	2-4, 6, 8, 9, 12-13	5, 10	8, 11 volumetric (arsenite, FAS)
Copper	3, 4, 7-9	1, 2	1, 3, 4, 8, 11 gravimetric (dimethyl glyoxime)
Cobalt	1-3, 5, 6, 8, 10, 11, 13	4, 12	7, 13 photometric (dimethyl glyoxime)
Niobium	1-9, 13	12	1, 2, 4, 6, 9, 10 volumetric (ferrous ammonium sulfate)
Tantalum	1-6	-	5 photometric (diphenyl carbazide)
Vanadium	1, 2, 4, 6, 9-11, 13	5, 7, 12	1, 7, 11, 14 photometric (thiocyanate)
Nitrogen	-	-	5, 6 photometric (BCO)
			7 gravimetric (oxide)
			9 photometric (2 β -naphthol)
			10 photometric (chlorosulfophenol)
			11 gravimetric
			3, 8 volumetric (ferrous ammonium sulfate)
			1, 2 photometric (nessler reagent)
			3, 5, 6 inert gas fusion (thermal conductivity)
			4 volumetric (hydrochloric acid)

Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2015 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

This certification is applicable to the whole of the disc. However, in accordance with normal practice for OES, it is appropriate to avoid usage of the central portion of ~ 8mm diameter.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in April 2036, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by L Maxim, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.