

MBH[®]

ANALYTICAL LTD

HOLLAND HOUSE • QUEENS ROAD • BARNET • EN5 4DJ • ENGLAND • TEL: 44 (0)20 8441 2024 • FAX: 44 (0)20 8449 0810
E-mail: info@mbh.co.uk Website http://www.mbh.co.uk

CERTIFICATE OF ANALYSIS

Reference Material Type

AUSTENITIC STAINLESS STEEL (CAST)

Catalogue Section: 13X

Sample No: 19004

Batch No: B

Certified Values

ELEMENT	C	Si	S	P	Mn	Ni
%	0.066	0.36	0.014	0.069	1.96	17.9
ELEMENT	Cr	Mo	Cu	Nb		
%	22.8	3.62	0.022	0.18		

Form and Size:

Disc 40mm diameter x 15mm thickness

Supplied by:

MBH Analytical Limited

Produced by:

Willan Metals Limited

Date of Certification:

18 July 1996

Intended Use:

With Optical Emission and X-Ray Fluorescence Spectrometers.

Recommended

Method of Use:

Steels are generally prepared by finishing (avoiding contamination with abrasives), milling or turning on a lathe avoiding the use of lubricants) or lapping (using a suitable polishing media). However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer. Preparation should be the same for reference materials and the samples for test. When using O.E. a minimum of three consistent replicate analyses is recommended to optimise precision and accuracy. Users are advised to check against possible bias between reference materials and production samples due to difference in metallurgical history and be aware of possible inter-element effect.

MBH ANALYTICAL LIMITED

Directors: D. Moore, D.J.R. Wood, C. Eveleigh

VAT Registered No. GB 421 329532 • Registered in England, No. 1875853 • Registered Office: Regency House, 33 Wood Street, Barnet EN5 4BE



Cert. No. 524

Method of Preparation: This Reference Material was produced from pure metals, ferro alloys and master alloys. The discs are the product of one melt poured into a single mould with feeding system designed to ensure sound discs. Metal was removed from the cast surface of the discs to minimise surface effect.

Sampling: Samples were taken relative to the top and the bottom of the mould. Two discs were used for chemical analysis and were checked for homogeneity.

Chemical Analysis Data:

Sample	C	Si	S	P	Mn	Ni	Cr
1	0.064	0.36	0.013	0.065	2.00	17.89	22.92
2	0.069	0.36	0.015	0.073	1.91	17.64	22.80
3	0.066	0.35	0.013	0.069	1.96	17.90	22.70
4	0.063	0.35	0.013	0.068	1.96	18.10	22.78
Mean:	0.066	0.36	0.014	0.069	1.96	17.88	22.80
Stand. Deviation:	0.003	0.006	0.001	0.003	0.037	0.188	0.091

Sample	Mo	Cu	Nb
1	3.56	-	0.17
2	3.59	0.025	0.19
3	3.63	0.020	0.15
4	3.68	0.022	0.20
Mean:	3.62	0.022	0.18
Standard Dev.	0.052	0.003	0.022

Homogeneity: Discs were taken relative to the top and bottom of the composite mould and each disc was checked on the face and back using an Optical Emission Spectrometer.

Multiple sparkings were made on each surface and averaged

The mean value of the material was then calculated from these averages.

The difference between the average for each step and the overall mean value is tabulated below in % concentration for each element.

Disc from Top of Mould

Position	C	Si	S	P	Mn	Ni
Face	0.000	-0.005	+0.001	-0.001	+0.01	+0.04
Back	-0.001	+0.015	-0.001	+0.002	-0.01	-0.01
Avge.	-0.001	+0.005	0.000	+0.001	0.00	+0.01

Position	Cr	Mo	Cu	Nb
Face	+0.03	+0.02	+0.007	+0.010
Back	-0.03	0.00	-0.007	0.000
Avge.	0.00	+0.01	0.000	+0.005

Disc from Bottom of Mould

Position	C	Si	S	P	Mn	Ni
Face	+0.001	+0.005	-0.001	+0.001	0.00	-0.03
Back	0.000	-0.015	+0.001	-0.002	0.00	0.00
Avge.	+0.001	-0.005	0.000	-0.001	0.00	-0.01

Position	Cr	Mo	Cu	Nb
Face	+0.02	+0.01	0.000	-0.010
Back	-0.03	-0.03	0.000	0.000
Avge.	0.00	-0.01	0.000	-0.005

Participating Laboratories:

Willan Metals Limited	Rotherham, England	NAMAS Approval 0014
J B Elds Limited	Stoke-on-Trent, England	NAMAS Approval 1173
Metals Tech (Testing) Ltd	Sheffield, England	NAMAS Approval 0963
MTS Teeside Limited	Middlesbrough, England	NAMAS Approval 0239

Analytical Methods Used:

Carbon	(a)	Combustion (IRD)		
Silicon	(a) (b)	Atomic Absorption	ICP	
Sulphur	(a)	Combustion (IRD)		
Phosphorus	(a) (b)	Colorimetric	Volumetric	ICP
Manganese	(a) (b)	Atomic Absorption	ICP	
Nickel	(a) (b)	Volumetric	ICP	
Chromium	(a) (b)	Volumetric	ICP	
Molybdenum	(a) (a)	Atomic Absorption	ICP	
Copper	(a) (b)	Atomic Absorption	ICP	
Niobium	(a) (b)	Atomic Absorption	ICP	

NOTE :

1. Some materials may exhibit shrinkage cavities on the rear engraved surface of the disc. This does not effect the certified portion.
2. (a) Overchecked by OES
(b) Overchecked by XRF
3. Confidence Limits

These are the upper and lower values between which the actual measurements will fall with a certain probability to a gaussian distribution

68.3% of the results will fall within ± 1 x Standard Deviation of the mean

95.4% of the results with fall within ± 2 x Standard Deviation of the mean

99.7% of the results will fall within ± 3 x Standard Deviation of the mean

The material to which the Certificate of Analysis refers is supplied subject to our general conditions of sale.