

# CERTIFICATE OF ANALYSIS

**13X 44004 (batch B)**

## Certified Reference Material Information

Type: FERRITIC STAINLESS STEEL (WROUGHT)  
Form and Size: Disc, 40mm diameter  
Manufactured by: Gloria Material Technology Corp, Taiwan  
Certified and Supplied by: MBH Analytical Ltd

## Assigned Values

### Percentage element by weight

Element	C	Si	S	P	Mn	Ni	Cr	Mo
Value <sup>1</sup>	1.012	0.440	0.0018	0.0232	0.378	0.197	16.50	0.468
Uncertainty <sup>2</sup>	0.015	0.006	0.0002	0.0009	0.005	0.004	0.04	0.003

Element	Cu	Co	V	W	Nb	Ti	Al	N
Value <sup>1</sup>	0.0687	0.0167	0.0484	0.0156	0.008	(0.004)	0.0160	0.0308
Uncertainty <sup>2</sup>	0.0014	0.0012	0.0014	0.0009	0.001	-	0.0013	0.0014

Note: values in parentheses are not certified; they are provided for information only

## Definitions

- <sup>1</sup> The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- <sup>2</sup> The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

## Certified by:

MBH ANALYTICAL LIMITED \_\_\_\_\_

on 4<sup>th</sup> January 2019

C Eveleigh

## **Method of Preparation**

This reference material was produced from commercial barstock to DIN 1.4125, equivalent to ASTM A276 440C, UNS S44004. The steel was prepared by electric arc melting and vacuum oxygen decarburization. The detail bar preparation procedures are unknown.

## **Sampling**

Samples for chemical analysis were taken from various positions throughout the batch. Approximately 5% of all discs were selected for non-destructive homogeneity testing.

## **Homogeneity**

The discs were checked for lateral segregation, and for local and batch homogeneity using an optical emission spectrometer.

Using the combined data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

## **Chemical Analysis**

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories operating within the terms of EN ISO/IEC 17025, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

## **Estimation of Uncertainties**

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ( $C_{(95\%)}$ ) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

## **Traceability**

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

Of the individual results herein, some have traceability (to the mole) via primary analytical methods. Some are traceable to substances of known stoichiometry. Most have traceability via commercial solutions. Furthermore, some results have additional traceability to NIST standards, as part of the analytical calibration or process control.

## **Usage**

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Steels are generally prepared by finishing, grinding, turning or milling. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

The recommended sample size is at least five replicate analyses. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

## Analytical Data

### Percentage element by weight

Sample	C	Si	S	P	Mn	Ni	Cr	Mo
1	0.973	0.4237	0.00125	0.0204	0.3630	0.1853	16.41	0.4596
2	0.991	0.4275	0.00130	0.0207	0.3660	0.1862	16.42	0.4601
3	0.996	0.4280	0.00154	0.0211	0.3720	0.1865	16.45	0.4626
4	0.998	0.4319	0.00157	0.0214	0.3746	0.1932	16.46	0.4670
5	1.010	0.4337	0.00160	0.0217	0.3763	0.1950	16.47	0.4680
6	1.012	0.4420	0.00160	0.0222	0.3780	0.1956	16.48	0.4684
7	1.013	0.4420	0.00180	0.0232	0.3805	0.2004	16.49	0.4690
8	1.014	0.4443	0.00197	0.0235	0.3830	0.2010	16.52	0.4700
9	1.016	0.4462	0.00198	0.0236	0.3840	0.2020	16.53	0.4715
10	1.022	0.4480	0.00200	0.0238	0.3845	0.2020	16.54	0.4725
11	1.022	0.4490	0.00210	0.0239	0.3856	0.2033	16.54	0.4727
12	1.023	0.4500	0.00220	0.0241	0.3860	0.2040	16.56	0.4770
13	1.030	0.4534	0.00228	0.0247		0.2053	16.56	
14	1.053			0.0248			16.59	
15				0.0255				
16				0.0259				
<b>Mean</b>	<b>1.012</b>	<b>0.4400</b>	<b>0.00178</b>	<b>0.0232</b>	<b>0.3778</b>	<b>0.1969</b>	<b>16.50</b>	<b>0.4682</b>
<b>Std Dev</b>	0.019	0.0098	0.00033	0.0017	0.0077	0.0072	0.06	0.0053
<b>C (95%)</b>	0.011	0.0059	0.00020	0.0009	0.0049	0.0043	0.03	0.0033

Sample	Cu	Co	V	W	Nb	Ti	Al	N
1	0.0650	0.0135	0.0451	0.0133	0.0052	0.0011	0.0142	0.0282
2	0.0653	0.0143	0.0453	0.0146	0.0061	0.0022	0.0146	0.0285
3	0.0656	0.0148	0.0471	0.0148	0.0061	0.0025	0.0148	0.0291
4	0.0661	0.0152	0.0478	0.0148	0.0063	0.0029	0.0148	0.0302
5	0.0664	0.0154	0.0482	0.0152	0.0069	0.0032	0.0149	0.0311
6	0.0678	0.0158	0.0483	0.0156	0.0073	0.0047	0.0156	0.0318
7	0.0681	0.0166	0.0488	0.0156	0.0076	0.0052	0.0162	0.0326
8	0.0692	0.0170	0.0488	0.0159	0.0084	0.0053	0.0166	0.0326
9	0.0695	0.0172	0.0491	0.0159	0.0086	0.0061	0.0173	0.0328
10	0.0704	0.0179	0.0492	0.0160	0.0089	0.0064	0.0184	
11	0.0706	0.0180	0.0496	0.0163	0.0100	0.0072	0.0190	
12	0.0708	0.0181	0.0508	0.0165	0.0105			
13	0.0715	0.0183	0.0515	0.0165	0.0107			
14	0.0717	0.0187		0.0178	0.0107			
15	0.0729	0.0192						
<b>Mean</b>	<b>0.0687</b>	<b>0.0167</b>	<b>0.0484</b>	<b>0.0156</b>	<b>0.0081</b>	<b>0.0043</b>	<b>0.0160</b>	<b>0.0308</b>
<b>Std Dev</b>	0.0026	0.0017	0.0018	0.0011	0.0019	0.0020	0.0016	0.0018
<b>C (95%)</b>	0.0014	0.0010	0.0011	0.0006	0.0011	0.0013	0.0011	0.0014

Note:  $C_{(95\%)}$  is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

## Participating Laboratories

Element Ltd	Middlesbrough, England	UKAS accreditation 0239
Sheffield Analytical Services	Sheffield, England	UKAS accreditation 0012
Metals Technology (Testing) Ltd	Sheffield, England	UKAS accreditation 0963
Anchorcert Analytical	Birmingham, England	UKAS accreditation 0667
Laboratory Testing, Inc	Hatfield, PA, USA	A2LA accreditation 0117
Universal Scientific Laboratory Pty Ltd	Milperra, NSW, Australia	NATA accreditation 0492
Genitest, Inc	Montreal, Canada	PJ accreditation L17-153
Shanghai Jinyi Test Tech Co	Shanghai, China	CNAS accreditation 0041
Luo Yang Copper	Luo Yng, He Nan, China	CNAL accreditation 0173
Raghavendra SpectroMet Laboratory	Bangalore, India	NABL accreditation 0371
TCR Engineering Services Ltd	Mumbai, India	NABL accreditation 0367
Gesra Labs India Pvt	Chennai, India	NABL accreditation 6238
Instytut Metalurgii Zelaza	Gliwice, Poland	PCA accreditation AB554
Tec-Eurolab	Campogalliano, Italy	ACCREDIA accreditation 52
TUV Nord Czech	Brno, Czech Republic	CAI accreditation L1060
INCDMNR-IMNR	Pantelimon, Romania	
Mineral & Metallurgical Laboratories	Bangalore, India	
AMG Superalloys UK Ltd	Rotherham, England	
Analyticka Laborator Lithea sro	Brno, Czech Republic	

Note: to achieve the above accreditation (UKAS, etc), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

## Analytical Methods Used

ELEMENT	RESULT No. & METHOD			
	ICP-AES	FAAS		OTHER
Carbon	-	-	all	combustion (IR or volumetric detection)
Silicon	1, 2, 4, 5, 9, 11, 13	-	6, 8, 10	gravimetric (perchloric acid)
			3, 7, 12	photometric (molybdenum blue)
Sulfur	8, 11, 13	-	1-7, 9, 10, 12	combustion (IR or volumetric detection)
Phosphorus	2-7, 10, 12, 13, 16	-	1, 14, 15	volumetric (alkalimetric)
			8, 9, 11	photometric (molybdenum blue)
Manganese	1, 2, 5, 7, 8, 10-12	6, 9	3, 4	volumetric (arsenite)
Nickel	1-4, 6, 7, 9, 11-13	-	5, 10	volumetric (dimethyl glyoxime, EDTA)
			8	gravimetric (dimethyl glyoxime)
Chromium	2, 3, 9, 13, 14	4	1, 5-8, 10-12	volumetric (ferrous ammonium sulfate)
Molybdenum	1-3, 5, 8-11	7	4, 6, 12	photometric (thiocyanate)
Copper	1, 5-9, 11, 13, 14	3, 4, 10, 15	2	photometric (BCO)
			12	volumetric (thiosulfate)
Cobalt	1, 3-6, 8-11, 13, 15	2, 7, 14	12	photometric (5CI-PADAB)
Vanadium	1-4, 7, 8, 10-13	5, 9	6	volumetric (ferrous ammonium sulfate)
Tungsten	3-5, 7-14	6	1	gravimetric
			2	photometric (thiocyanate)
Niobium	1, 2, 4-6, 8-12, 14	7, 14	3	photometric (chlorosulfophenol)
			13	gravimetric
Titanium	1, 2, 5, 6, 8-10	7, 11	3, 4	photometric (diantipyryl methane)
Aluminium	1-3, 5-8	9	4	volumetric (EDTA)
			10	photometric (chrome azurol S)
Nitrogen	-	-	1-6, 8, 9	inert gas fusion (thermal conductivity)
			7	photometric (Nessler reagent)

## Notes

This Certified Reference Material has been produced and certified, wherever possible, in accordance with the requirements of ISO 17034 and the associated Guides, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

This certification is applicable to the whole of the disc. However, in accordance with normal practice for emission spectrometry, it is appropriate to avoid usage of the centre of the disc, ~8 mm diameter.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in January 2039, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings, for the assessment and calibration of 'wet' analytical techniques.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.