

# CERTIFICATE OF ANALYSIS

## 14X FeNi50 (batch C)

### Certified Reference Material Information

Type: IRON-NICKEL ALLOY (CHILL-CAST)  
Form and Size: Disc ~40mm diameter  
Manufactured by: Polycast Ltd  
Certified and Supplied by: MBH Analytical Ltd

### Assigned Values

#### Percentage element by weight

Element	C	Si	S	P	Mn
Value <sup>1</sup>	0.0245	0.151	0.16	0.0168	0.0571
Uncertainty <sup>2</sup>	0.0008	0.004	0.01	0.0009	0.0012

Element	Ni	Cr	Cu	Co	Al
Value <sup>1</sup>	51.56	0.0662	0.089	0.416	0.319
Uncertainty <sup>2</sup>	0.12	0.0016	0.002	0.007	0.009

### Definitions

- <sup>1</sup> The assigned values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- <sup>2</sup> The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

### Certified by:

MBH ANALYTICAL LIMITED \_\_\_\_\_  
C Eveleigh

on 1<sup>st</sup> August 2018

## **Method of Preparation**

This reference material was produced from commercial metals, with the minor and trace elements added as pure elements or master alloys. The discs are the product of one melt poured into multiple chill moulds with feeding systems designed to ensure sound discs. Approximately 2mm has been removed from the cast faces of the discs to minimise surface effects.

## **Sampling**

Samples for chemical analysis were taken from various positions throughout the casting process. At least 15% of the discs were selected for non-destructive homogeneity testing.

## **Homogeneity**

The discs were checked for sample and batch uniformity using an optical emission spectrometer.

Using the meaned data for each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

## **Chemical Analysis**

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

## **Estimation of Uncertainties**

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ( $C_{(95\%)}$ ) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

## **Traceability**

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials.

Of the individual results herein, some have traceability (to the mole) via primary analytical methods. Some are traceable to substances of known stoichiometry. Most have traceability via commercial solutions. Furthermore, some results have additional traceability to NIST standards, as part of the analytical calibration or process control.

## **Usage**

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Steels are generally prepared by grinding. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer. Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

## Analytical Data

### Percentage element by weight

Sample	C	Si	S	P	Mn
1	0.0227	0.1440	0.1466	0.0145	0.0542
2	0.0230	0.1450	0.1580	0.0156	0.0546
3	0.0237	0.1456	0.1580	0.0156	0.0550
4	0.0241	0.1460	0.1581	0.0157	0.0559
5	0.0242	0.1498	0.1590	0.0157	0.0576
6	0.0243	0.1501	0.1609	0.0161	0.0576
7	0.0244	0.1524	0.1610	0.0163	0.0578
8	0.0248	0.1527	0.1620	0.0164	0.0578
9	0.0255	0.1550	0.1700	0.0167	0.0580
10	0.0257	0.1557	0.1751	0.0168	0.0581
11	0.0260	0.1571		0.0177	0.0587
12	0.0260	0.1590		0.0190	0.0598
13				0.0195	
14				0.0198	
<b>Mean</b>	<b>0.0245</b>	<b>0.1510</b>	<b>0.1609</b>	<b>0.0168</b>	<b>0.0571</b>
<b>Std Dev</b>	0.0011	0.0051	0.0076	0.0016	0.0017
<b>C<sub>(95%)</sub></b>	0.0007	0.0032	0.0054	0.0009	0.0011

Sample	Ni	Cr	Cu	Co	Al
1	51.38	0.0630	0.0839	0.4006	0.2988
2	51.38	0.0630	0.0844	0.4007	0.2997
3	51.38	0.0634	0.0870	0.4042	0.3030
4	51.51	0.0651	0.0874	0.4085	0.3091
5	51.53	0.0653	0.0875	0.4090	0.3168
6	51.55	0.0653	0.0885	0.4152	0.3200
7	51.57	0.0659	0.0896	0.4166	0.3220
8	51.63	0.0665	0.0898	0.4180	0.3233
9	51.72	0.0666	0.0904	0.4209	0.3303
10	51.76	0.0674	0.0905	0.4270	0.3313
11	51.79	0.0681	0.0910	0.4280	0.3320
12		0.0685	0.0910	0.4296	0.3420
13		0.0686	0.0937	0.4298	
14		0.0696			
<b>Mean</b>	<b>51.56</b>	<b>0.0662</b>	<b>0.0888</b>	<b>0.4160</b>	<b>0.3190</b>
<b>Std Dev</b>	0.15	0.0021	0.0028	0.0107	0.0140
<b>C<sub>(95%)</sub></b>	0.10	0.0012	0.0017	0.0065	0.0089

Note: C<sub>(95%)</sub> is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

## Participating Laboratories

Exova Ltd	Middlesbrough, England	UKAS accreditation 0239
Sheffield Assay Office	Sheffield, England	UKAS accreditation 0012
Anchorcert Analytical	Birmingham, England	UKAS accreditation 0667
Metals Technology (Testing) Ltd	Sheffield, England	UKAS accreditation 0963
Laboratory Testing, Inc	Hatfield, PA, USA	A2LA accreditation 0117
Genitest Inc	Montreal, Canada	PJ accreditation L17-153
Universal Scientific Laboratory Pty Ltd	Sydney, Australia	NATA accreditation 492
Shanghai Jinyi Test Tech Co	Shanghai, China	CNAS accreditation L0041
Shandong Metallurgical & Science Research	Shandong, Jinan, China	CNAS accreditation 1461
Raghavendra SpectroMet Laboratory	Bangalore, India	NABL accreditation T371
Tec-Eurolab	Campogalliano, Italy	ACCREDIA accreditation 52
Instytut Metalurgii Zelaza	Gliwice, Poland	PCA accreditation AB554
TUV Nord Czech	Brno, Czech Republic	CAI accreditation L1060
Mineral & Metallurgical Laboratories	Bangalore, India	
AMG Superalloys UK Ltd	Rotherham, England	
Analyticka Laborator Lithea sro	Brno, Czech Republic	

Note: to achieve the above accreditation (UKAS, etc), test houses are required to demonstrate conformity to the general requirements of EN ISO/IEC 17025.

## Analytical Methods Used

ELEMENT	RESULT No. & METHOD		
	ICP-AES	FAAS	OTHER
Carbon	-	-	all combustion (IR or volumetric detection)
Silicon	3-5, 7, 8, 10, 11	-	1, 2, 9 photometric (molybdenum blue)
			6, 12 gravimetric (perchloric acid)
Sulfur	-	-	1-10 combustion (IR or volumetric detection)
Phosphorus	2, 3, 7-12, 14	-	1, 4, 5 photometric (molybdenum blue)
			6, 13 volumetric (alkalimetric)
Manganese	3-9, 11, 12	1, 10	2 volumetric (arsenite)
Nickel	2, 3, 7, 8, 10	-	1, 4-6, 9, 11 gravimetric (dimethyl glyoxime)
Chromium	2, 3, 6-8, 11-14	1, 5	4, 9, 10 volumetric (ferrous ammonium sulfate)
Copper	1-3, 5-7, 11-13	4, 8	10 photometric (BCO)
			9 volumetric (thiosulfate)
Cobalt	1-4, 6, 7, 12, 13	8, 9	5, 10 photometric (2 $\beta$ -naphthol)
			11 gravimetric
Aluminium	1-6, 8, 10	9, 12	7 photometric (chrome azurol S)
			11 volumetric (EDTA)

## Notes

This Certified Reference Material has been produced and certified, wherever possible, in accordance with the requirements of ISO Guide 34, ISO Guide 31 and ISO Guide 35, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with this method of chill casting have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face of the disc to a depth of 10mm. Material to the rear of the disc, to a depth of ~5 mm, is not certified.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in August 2038, although we reserve the right to make changes as issue revisions, in the intervening period.

This product is also available in the form of chips, for use in the control of 'wet' analytical techniques.

The specification, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.