

CERTIFICATE OF ANALYSIS

14X FeNi8 (batch A)

Certified Reference Material Information

Type: IRON-NICKEL ALLOY (WROUGHT)
Form and Size: Disc ~40mm diameter
Manufactured by: Polycast Ltd
Certified and Supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

Element	C	Si	S	P	Mn
Value ¹	0.0974	0.099	0.0284	0.0151	0.333
Uncertainty ²	0.0019	0.002	0.0009	0.0007	0.005

Element	Ni	Cr	Cu	Al	N
Value ¹	8.11	0.251	0.0304	0.030	0.0062
Uncertainty ²	0.04	0.005	0.0013	0.001	0.0003

Definitions

- ¹ The assigned values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- ² The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:

MBH ANALYTICAL LIMITED _____

on 24th May 2016

L Maxim



Method of Preparation

This reference material was produced from commercial-purity metals and master alloys. The discs are the product of one melt, cast into 70mm diameter billets and hot worked into bars of ~42mm diameter.

Sampling

Milled samples for chemical analysis were taken from several positions within the batch. In addition, at least 15% of all discs were selected for homogeneity checking.

Homogeneity

Samples representative of the batch were checked for uniformity using an optical emission spectrometer. Multiple measurements were taken from each surface under test.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Steels are generally prepared by finishing, grinding, turning or milling. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer. Preparation should be the same for reference materials and the samples for test.

For optical emission spectroscopy, a minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

Sample	C	Si	S	P	Mn
1	0.0938	0.0956	0.0265	0.0140	0.3210
2	0.0943	0.0974	0.0270	0.0142	0.3300
3	0.0943	0.0978	0.0273	0.0145	0.3307
4	0.0959	0.0978	0.0273	0.0146	0.3320
5	0.0970	0.0980	0.0274	0.0146	0.3335
6	0.0976	0.0984	0.0278	0.0151	0.3348
7	0.0977	0.0995	0.0283	0.0151	0.3370
8	0.0982	0.0998	0.0285	0.0154	0.3370
9	0.0984	0.0998	0.0285	0.0162	0.3383
10	0.0986	0.1003	0.0288	0.0162	0.3388
11	0.0986	0.1009	0.0292	0.0165	
12	0.1004		0.0293		
13	0.1012		0.0297		
14			0.0303		
15			0.0305		
Mean	0.0974	0.0987	0.0284	0.0151	0.3333
Std Dev	0.0023	0.0015	0.0012	0.0009	0.0053
C_(95%)	0.0014	0.0010	0.0007	0.0006	0.0038

Sample	Ni	Cr	Cu	Al	N
1	8.014	0.2367	0.0275	0.0286	0.0056
2	8.035	0.2411	0.0278	0.0291	0.0059
3	8.055	0.2462	0.0285	0.0296	0.0060
4	8.075	0.2470	0.0289	0.0297	0.0060
5	8.085	0.2470	0.0292	0.0301	0.0061
6	8.100	0.2500	0.0305	0.0304	0.0064
7	8.109	0.2504	0.0307	0.0304	0.0065
8	8.120	0.2530	0.0312	0.0309	0.0068
9	8.120	0.2540	0.0315		0.0069
10	8.123	0.2550	0.0315		
11	8.154	0.2571	0.0317		
12	8.193	0.2574	0.0319		
13	8.200	0.2577	0.0321		
14		0.2578	0.0321		
Mean	8.106	0.2507	0.0304	0.0299	0.0062
Std Dev	0.055	0.0065	0.0017	0.0008	0.0004
C_(95%)	0.034	0.0038	0.0010	0.0007	0.0003

Note: C_(95%) is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Exova Ltd	Middlesbrough, UK	UKAS accreditation	0239
Sheffield Analytical Services	Sheffield, UK	UKAS accreditation	0012
Metals Technology (Testing) Ltd	Sheffield, UK	UKAS accreditation	0963
Universal Scientific Laboratory Pty Ltd	Milperra, NSW, Australia	NATA accreditation	0492
Genitest Inc.	Montreal, QC, Canada	PRI accreditation	123077
Shanghai JinYi Test Technology Co. Ltd	Shanghai, China	CNAL accreditation	0783
Shandong Metallurgical & Science Research Bureau Veritas CPS Ltd	Jinan, Shandong, China	CNAS accreditation	1461
TCR Engineering Services pvt Ltd	Chennai, India	NABL accreditation	0025
Raghavendra Spectro Metallurgical Laboratory	Mumbai, India	NABL accreditation	0367
Instytut Metalurgii Zelaza	Bangalore, India	NABL accreditation	0371
TEC Eurolab SRL	Gliwice, Poland	PCA accreditation	AB554
AMG Superalloys UK Ltd	Modena, Italy	ACCREDIA accreditation	52
Analyticka Laborator Lithea sro	Rotherham, UK		
Coleshill Laboratories Ltd	Brno, Czech Republic		
	Coleshill, UK		

Note: to achieve the above accreditation (UKAS, NATA, etc), test houses are required to demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT	RESULT No. & METHOD		
	ICP-AES	FAAS	OTHER
Carbon	-	-	all combustion (infra-red detection)
Silicon	1, 4, 6, 10, 11	-	2, 3 gravimetric (perchloric acid)
Sulfur	5, 6, 9	-	5, 7-9 photometric (molybdenum blue)
Phosphorus	2-7, 9	-	1-4, 7, 8, 10-15 combustion (infra-red detection)
Manganese	1, 3, 5-9	2	1, 8, 11 photometric (molybdenum blue)
Nickel	1, 2, 4, 9-12	6, 13	10 volumetric (alkalimetric)
Chromium	1, 2, 4, 5, 7, 10-12, 14	3, 6, 13	4 volumetric (arsenite)
Copper	1, 2, 5, 6, 8-10, 12, 14	3, 4, 11	10 photometric (periodate)
Aluminium	1, 4, 7, 8	2, 6	3, 8 photometric (dimethyl glyoxime)
Nitrogen	-	-	5, 7 gravimetric (dimethyl glyoxime)
			8 volumetric (FAS)
			9 photometric (diphenyl carbazide)
			7, 13 photometric (BCO)
			3, 5 photometric (chrome azurol S)
			1, 2 volumetric (hydrochloric acid)
			3, 4, 6-8 inert gas fusion (thermal conductivity)
			5, 9 photometric (nessler reagent)

Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2015 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

This certification is applicable to the whole of the disc. However, in accordance with normal practice for OES, it is appropriate to avoid usage of the central portion of ~ 8mm diameter.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in May 2036, although we reserve the right to make changes as issue revisions, in the intervening period.

This material is also available in the form of chippings

The manufacture, analysis and certification of this product were supervised by L Maxim, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.