

CERTIFICATE OF ANALYSIS

212X 04400 (batch A)

Certified Reference Material Information

Type: MONEL alloy 400 (WROUGHT)
Form and Size: Disc 40mm diameter
Manufactured by: Special Metals Wiggin Ltd, UK
Certified and Supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

Element	C	Si	S	P	Mn	Cu	Cr	Fe
Value ¹	0.157	0.253	(0.002)	0.0033	1.027	32.47	0.166	2.065
Uncertainty ²	0.003	0.009	-	0.0004	0.012	0.09	0.004	0.012

Element	Mo	Co	Ti	Al	Mg	B	Ni	N
Value ¹	0.0307	0.0432	0.0193	0.030	0.053	0.0019	63.69	0.0005
Uncertainty ²	0.0010	0.0024	0.0010	0.002	0.002	0.0002	0.15	0.0001

Note: values given in parentheses are not certified - they are provided for information only.

Definitions

- ¹ The above values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- ² The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:

MBH ANALYTICAL LIMITED _____

on 26th November 2012

C Eveleigh

Method of Preparation

This reference material was produced from commercial barstock to UNS N04400 hot extruded and annealed. The discs are the product of one length of bar.

Sampling

Samples for chemical analysis were taken from various positions within the bar. At least 15% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

The discs were checked for sample and batch uniformity using an optical emission spectrometer.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Nickel-base alloys are generally prepared by finishing, milling, turning or polishing. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

For OES, a minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

Sample	C	Si	S	P	Mn	Cu	Cr	Fe
1	0.153	0.232	0.0010	0.0023	1.000	32.34	0.159	2.043
2	0.153	0.240	0.0011	0.0025	1.004	32.39	0.159	2.046
3	0.154	0.242	0.0013	0.0029	1.017	32.42	0.160	2.055
4	0.154	0.242	0.0015	0.0031	1.025	32.42	0.161	2.056
5	0.156	0.253	0.0018	0.0032	1.026	32.43	0.165	2.064
6	0.157	0.253	0.0018	0.0035	1.028	32.44	0.166	2.065
7	0.158	0.255	0.0022	0.0036	1.030	32.49	0.167	2.071
8	0.159	0.257	0.0023	0.0037	1.030	32.51	0.168	2.075
9	0.160	0.265	0.0023	0.0040	1.033	32.52	0.169	2.077
10	0.160	0.270	0.0030	0.0040	1.037	32.60	0.173	2.080
11	0.162	0.271	0.0030		1.045	32.65	0.174	2.083
12			0.0033		1.049		0.175	
Mean	0.157	0.253	0.0021	0.0033	1.027	32.47	0.166	2.065
Std Dev	0.003	0.013	0.0007	0.0006	0.015	0.09	0.006	0.014
C_(95%)	0.002	0.009	0.0005	0.0004	0.009	0.06	0.004	0.009

Sample	Mo	Co	Ti	Al	Mg	B	Ni	N
1	0.0284	0.0392	0.0168	0.0258	0.0501	0.0015	63.50	0.0002
2	0.0292	0.0400	0.0178	0.0267	0.0502	0.0017	63.63	0.0004
3	0.0294	0.0402	0.0181	0.0280	0.0508	0.0017	63.63	0.0004
4	0.0295	0.0420	0.0184	0.0285	0.0518	0.0018	63.69	0.0004
5	0.0297	0.0424	0.0189	0.0290	0.0520	0.0019	63.75	0.0006
6	0.0303	0.0453	0.0190	0.0295	0.0531	0.0020	63.80	0.0006
7	0.0306	0.0461	0.0196	0.0297	0.0536	0.0020	63.82	0.0006
8	0.0309	0.0470	0.0200	0.0298	0.0540	0.0024		<0.001
9	0.0317	0.0470	0.0202	0.0308	0.0550			<0.001
10	0.0326		0.0210	0.0316	0.0560			
11	0.0330		0.0210	0.0320	0.0564			
12	0.0330		0.0211	0.0323				
13				0.0332				
Mean	0.0307	0.0432	0.0193	0.0298	0.0530	0.0019	63.69	0.0005
Std Dev	0.0016	0.0031	0.0014	0.0022	0.0022	0.0003	0.11	0.0002
C_(95%)	0.0010	0.0024	0.0009	0.0013	0.0015	0.0002	0.10	0.0001

Note: C_(95%) is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Exova Ltd	Middlesbrough, England	UKAS accreditation 0239
IncoTest Ltd	Hereford, England	UKAS accreditation 0281
Sheffield Assay Office	Sheffield, England	UKAS accreditation 0012
Metals Technology (Testing) Ltd	Sheffield, England	UKAS accreditation 0963
Laboratory Testing, Inc	Hatfield, PA, USA	A2LA accreditation 0117
Genitest, Inc	Montreal, Canada	PRI accreditation 123077
Institute of Iron and Steel Technology	Shanghai, China	CNAL accreditation 0783
Sargam Metals Pvt Ltd	Chennai, India	NABL accreditation 0025
TCR Engineering Services Ltd	Mumbai, India	NABL accreditation 0367
Raghavendra Spectrometallurgical Lab.	Bangalore, India	NABL accreditation 0371
Instytut Metalurgii Zelaza	Gliwice, Poland	PCA accreditation AB554
Tec-Eurolab	Campogalliano, Italy	ACCREDIA accreditation 52
London & Scandinavian Met. Co Ltd	Rotherham, England	
Coleshill Laboratories Ltd	Birmingham, England	
De Bruyn Spectroscopic Solutions Ltd	Johannesburg, South Africa	

Note: to achieve the above-noted accreditation (eg UKAS, A2LA, etc), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT	RESULT No. & METHOD			
	ICP-AES	FAAS		OTHER
Carbon	-	-	all	combustion (IR or volumetric detection)
Silicon	1, 5-8, 10, 11	-	2, 4, 9	gravimetric (perchloric acid)
			3	photometric (molybdenum blue)
Sulfur	1, 8	-	2-7, 9-12	combustion (IR or volumetric detection)
Phosphorus	1, 2, 5-12	-	3	photometric (molybdenum blue)
			4	ICP-MS
Manganese	2-4, 8-12	1, 7	5	volumetric (arsenite)
			6	photometric (periodate)
Copper	2-5, 7-10	-	1	volumetric (thiosulfate)
			6	electrogravimetric
			11	photometric (BCO)
Chromium	1, 2, 4, 6-10	3, 5	11, 12	volumetric (ferrous ammonium sulfate)
Iron	1, 2, 4-10	11	3	volumetric (dichromate)
Molybdenum	1, 3-7, 9-11	2, 8	12	photometric (thiocyanate)
Cobalt	1, 2, 5-9	3	4	volumetric (iodine)
Titanium	1-5, 7, 8, 10, 11	9, 12	6	photometric (DAP)
Aluminium	1-5, 7, 10-13	6, 9	8	photometric (chrome azurol S)
Magnesium	1, 3-11	2		
Boron	1-8	-		
Nickel	1-3, 5, 7	-	4	volumetric (EDTA/DMGO)
			6	gravimetric (dimethyl glyoxime)
Nitrogen	-	-	1-5, 8, 9	inert gas fusion (thermal conductivity)
			6, 7	photometric (Nessler's reagent)

Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2000 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

This certification is applicable to the whole of the disc. However, in accordance with normal practice for emission spectrometry, it is appropriate to avoid usage of the central portion of the disc, ~8 mm diameter.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. This certification will therefore expire in November 2032, although we reserve the right to make changes as issue revisions, in the intervening period.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.