

HOLLAND HOUSE • QUEENS ROAD • BARNET • EN5 4DJ • ENGLAND • TEL: +44 (0)20 8441 2024 • FAX: +44 (0)20 8449 0810 email: info@mbh.co.uk web: www.mbh.co.uk

CERTIFICATE OF ANALYSIS

212X 4004 (batch M)

Certified Reference Material Information

Type: NICKEL/COPPER MONEL-TYPE (CHILL CAST)

Form and Size: Disc ~40mm diameter

Manufactured by: Polycast Ltd

Certified and Supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

Element	С	Si	S	Р	Mn	Cu	Cr	Мо	Fe
Value ¹	0.081	0.557	0.0110	0.0400	0.953	29.0	0.822	0.197	3.68
Uncertainty ²	0.002	0.006	0.0010	0.0010	0.010	0.2	0.010	0.003	0.02

Element	Со	Nb	Ti	Al	Sn	Pb	Cd	Ni
Value ¹	0.0758	0.949	0.652	0.71	0.0596	0.0206	0.0010	62.1
Uncertainty 2	0.0009	0.006	0.008	0.02	0.0015	0.0006	0.0002	0.2

Definitions

- The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:		
MBH ANALYTICAL LIMITED_		on 12 th August 2014
	C Eveleigh	

Method of Preparation

This reference material was produced from commercial-purity metals, and master alloys. The discs are the product of one melt poured into a sequence of multiple chill moulds with feeding systems designed to ensure sound discs. Approximately 2mm has been removed from the cast faces of the discs to minimise surface effects.

<u>Sampling</u>

Samples for chemical analysis were taken from various positions throughout the casting process. At least 15% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

The discs were checked for sample and batch uniformity using an optical emission spectrometer.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals (C_(95%)) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use:

Nickel-base alloys are generally prepared by linishing, milling, turning or polishing. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

For OES, a minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

Sample	С	Si	S	Р	Mn	Cu	Cr	Мо	Fe
1	0.0770	0.547	0.0086	0.0378	0.942	28.89	0.805	0.191	3.629
2	0.0771	0.552	0.0099	0.0385	0.945	28.89	0.809	0.191	3.636
3	0.0782	0.552	0.0100	0.0390	0.947	28.94	0.811	0.191	3.643
4	0.0786	0.552	0.0100	0.0391	0.947	28.98	0.812	0.194	3.659
5	0.0788	0.556	0.0103	0.0394	0.948	29.05	0.821	0.194	3.678
6	0.0794	0.558	0.0106	0.0406	0.952	29.10	0.821	0.194	3.688
7	0.0794	0.558	0.0106	0.0410	0.953	29.17	0.823	0.195	3.688
8	0.0800	0.559	0.0109	0.0412	0.953	29.19	0.825	0.196	3.690
9	0.0800	0.560	0.0112	0.0414	0.953	29.19	0.827	0.200	3.693
10	0.0816	0.561	0.0131	0.0418	0.959		0.829	0.201	3.694
11	0.0821	0.565	0.0132		0.961		0.830	0.202	3.697
12	0.0841	0.567	0.0132		0.962		0.831	0.204	3.708
13	0.0850				0.965		0.831	0.206	
14	0.0860						0.834		
Mean	0.0805	0.557	0.0110	0.0400	0.953	29.04	0.822	0.197	3.675
Std Dev	0.0029	0.006	0.0015	0.0014	0.007	0.12	0.009	0.005	0.027
C _(95%)	0.0016	0.004	0.0009	0.0010	0.004	0.10	0.005	0.003	0.017

Sample	Co	Nb	Ti	Al	Sn	Pb	Cd	Ni
1	0.0734	0.944	0.637	0.698	0.0565	0.0196	0.0006	61.90
2	0.0738	0.946	0.644	0.698	0.0573	0.0198	0.0006	61.94
3	0.0747	0.946	0.649	0.700	0.0580	0.0201	8000.0	61.98
4	0.0747	0.947	0.650	0.700	0.0590	0.0203	0.0010	62.04
5	0.0751	0.948	0.652	0.703	0.0597	0.0207	0.0011	62.09
6	0.0754	0.948	0.654	0.705	0.0599	0.0209	0.0011	62.09
7	0.0754	0.948	0.654	0.706	0.0599	0.0211	0.0011	62.09
8	0.0756	0.948	0.654	0.708	0.0611	0.0212	0.0011	62.12
9	0.0761	0.951	0.658	0.715	0.0619	0.0218	0.0012	62.14
10	0.0763	0.955	0.658	0.715	0.0625		0.0013	62.17
11	0.0764	0.960	0.661	0.715				62.18
12	0.0772			0.719				62.22
13	0.0783			0.722				
14	0.0790							
Mean	0.0758	0.949	0.652	0.708	0.0596	0.0206	0.0010	62.08
Std Dev	0.0016	0.005	0.007	0.008	0.0019	0.0007	0.0002	0.10
C _(95%)	0.0009	0.003	0.005	0.005	0.0014	0.0006	0.0002	0.06

Note: $C_{(95\%)}$ is the 95% half-width confidence interval derived from the equation:

 $C_{(95\%)} = (t \times SD)/\sqrt{n}$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Exova Ltd
Sheffield Assay Office
Metals Technology (Testing) Ltd
Laboratory Testing, Inc
Shanghai Jinyi Test Tech Co
Shandong Metallurgical & Science Research
Bureau Veritas CPS Pvt
Raghavendra SpectroMet Laboratory
Genitest Inc
Tec-Eurolab
Instytut Metalurgii Zelaza
London & Scandinavian Met Co
Coleshill Laboratories Ltd
Lithea sro
Mineral & Metallurgical Laboratories

Middlesbrough, England Sheffield, England Sheffield, England Hatfield, PA, USA Shanghai, China Jinan, Shandong, China Chennai, India Bangalore, India Montreal, Canada Campogalliano, Italy Gliwice, Poland Rotherham, England Birmingham, England Brno, Czech Republic Bangalore, India UKAS accreditation 0239
UKAS accreditation 0012
UKAS accreditation 0963
A2LA accreditation 0117
CNAS accreditation L0041
CNAS accreditation 1461
NABL accreditation 0025
NABL accreditation T371
PRI accreditation 123077
ACCREDIA accreditation 52
PCA accreditation AB554

Note: to achieve the above accreditation (UKAS, NATA, etc), test houses are required to demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT	RESULT No. & METHOD								
	ICP-AES	FAAS		OTHER					
Carbon	-	-	all	combustion (IR or volumetric detection)					
Silicon	1, 3, 7-9, 11, 12	-	2	photometric (molybdenum blue)					
			4-6, 10	gravimetric (perchloric acid)					
Sulfur	-	-	all	combustion (IR or volumetric detection)					
Phosphorus	1, 3-10	-	2	volumetric (alkali metric)					
Manganese	1, 4-6, 8-13	7	2, 3	volumetric (arsenite)					
Copper	2, 3, 5, 6, 9	-	4	volumetric (thiosulfate)					
			1, 7, 8	electrogravimetric					
Chromium	1, 3, 4, 6, 9-12, 14	8, 13	2, 5, 7	volumetric (ferrous ammonium sulfate)					
Molybdenum	1-3, 5-8, 10-12	9	4	photometric (thiocyanate)					
			13	gravimetric (α benzoin oxime)					
Iron	2, 3, 5-8, 10-12	1, 4	9	volumetric (dichromate)					
Cobalt	1, 3-6, 8-13	7, 14	2	volumetric (iodine)					
Niobium	1-4, 7-11	-	5	photometric (chlorosulfophenol)					
			6	ICP-MS					
Titanium	1-5, 7-10	-	6, 11	photometric (di-antipyryl methane)					
Aluminium	2-8, 10-13	9	1	photometric (chrome azurol S)					
Lead	2-4, 6-9	1, 5							
Tin	1-9	10							
Cadmium	1-4, 7-10	5, 6							
Nickel	1, 7-9, 12	-	2-6, 10, 11	gravimetric (dimethyl glyoxime)					

Notes

This Certified Reference Material has been produced and certified, wherever possible, in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2000 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with chill casting have led to the formation of inhomogeneous segregates in the rear portion of the disc. However, testing has shown that the above certification is applicable from the front face of the disc to a depth of 10mm. Material to the rear of the disc, to a depth of ~5mm, is not certified.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in August 2034, although we reserve the right to make changes as issue revisions, in the intervening period.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.