

CERTIFICATE OF ANALYSIS

32X ALB10 (batch B)

Certified Reference Material Information

Type: ALUMINIUM BRONZE (CHILL CAST)
Form and Size: Disc ~40mm diameter
Manufactured by: Polycast Ltd
Certified and Supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

Element	Sn	Pb	Zn	Fe	Ni	Al	Mn	Si
Value ¹	0.201	0.152	0.961	3.63	7.21	12.11	1.626	0.158
Uncertainty ²	0.005	0.003	0.007	0.03	0.05	0.08	0.016	0.004

Element	Co	As	P	Mg	Cr	Ag	Te	Cu
Value ¹	0.0984	0.0194	0.069	0.0122	0.0152	0.0144	0.0108	73.64
Uncertainty ²	0.0012	0.0008	0.002	0.0008	0.0005	0.0006	0.0007	0.10

Definitions

- ¹ The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- ² The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:

MBH ANALYTICAL LIMITED _____

on 5th December 2016

C. Eveleigh

Method of Preparation

This reference material was produced from commercial-purity metals and master alloys. The discs are the product of one melt poured into multiple chill moulds with feeding systems designed to ensure sound discs. Approximately 2mm has been removed from the cast faces of the discs to minimise surface effects.

Sampling

Samples for chemical analysis were taken from various positions throughout the batch. At least 15% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

Samples representative of the batch were checked for uniformity using an optical emission spectrometer. Multiple measurements were taken from each surface under test.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, described above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials.

Of the individual results herein, some have traceability (to the mole) via primary analytical methods. Some are traceable to substances of known stoichiometry. Most have traceability via commercial solutions. Furthermore, some results have additional traceability to NIST standards, as part of the analytical calibration or process control.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Copper alloys are generally prepared by machining on a mill or a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

Sample	Sn	Pb	Zn	Fe	Ni	Al	Mn	Si
1	0.1917	0.1464	0.9442	3.600	7.158	11.973	1.602	0.1502
2	0.1920	0.1469	0.9501	3.602	7.168	12.008	1.605	0.1510
3	0.1939	0.1480	0.9520	3.603	7.190	12.051	1.613	0.1510
4	0.1950	0.1490	0.9560	3.612	7.193	12.060	1.616	0.1540
5	0.1990	0.1507	0.9574	3.617	7.197	12.067	1.622	0.1545
6	0.1998	0.1510	0.9590	3.626	7.201	12.089	1.622	0.1556
7	0.2010	0.1513	0.9601	3.627	7.206	12.140	1.624	0.1583
8	0.2030	0.1520	0.9613	3.630	7.213	12.140	1.635	0.1600
9	0.2031	0.1520	0.9616	3.636	7.216	12.143	1.636	0.1600
10	0.2064	0.1520	0.9627	3.639	7.233	12.160	1.638	0.1610
11	0.2073	0.1520	0.9652	3.640	7.237	12.181	1.644	0.1618
12	0.2094	0.1533	0.9652	3.641	7.259	12.230	1.660	0.1638
13	0.2117	0.1541	0.9703	3.659	7.280	12.250		0.1648
14		0.1584	0.9780					0.1686
15		0.1590	0.9790					
Mean	0.2010	0.1517	0.9615	3.626	7.212	12.115	1.626	0.1582
Std Dev	0.0066	0.0036	0.0095	0.018	0.034	0.083	0.017	0.0057
C_(95%)	0.0040	0.0020	0.0053	0.011	0.021	0.050	0.011	0.0033

Sample	Co	As	P	Mg	Cr	Ag	Te	Cu
1	0.0964	0.0178	0.0650	0.0114	0.0142	0.0136	0.0093	73.553
2	0.0965	0.0178	0.0663	0.0114	0.0143	0.0136	0.0097	73.570
3	0.0966	0.0184	0.0672	0.0115	0.0144	0.0136	0.0101	73.576
4	0.0968	0.0184	0.0676	0.0117	0.0147	0.0136	0.0102	73.590
5	0.0971	0.0186	0.0678	0.0118	0.0150	0.0142	0.0106	73.590
6	0.0972	0.0190	0.0692	0.0119	0.0151	0.0143	0.0109	73.605
7	0.0974	0.0190	0.0692	0.0123	0.0154	0.0143	0.0112	73.618
8	0.0980	0.0199	0.0699	0.0124	0.0154	0.0145	0.0119	73.650
9	0.0981	0.0199	0.0701	0.0125	0.0155	0.0149	0.0120	73.740
10	0.0994	0.0200	0.0722	0.0126	0.0156	0.0151	0.0123	73.780
11	0.0998	0.0202	0.0724	0.0128	0.0159	0.0155		73.820
12	0.0999	0.0204	0.0724	0.0135	0.0159	0.0158		
13	0.1000	0.0209	0.0730		0.0161			
14	0.1001	0.0211						
15	0.1001							
16	0.1003							
Mean	0.0984	0.0194	0.0694	0.0122	0.0152	0.0144	0.0108	73.645
Std Dev	0.0015	0.0011	0.0026	0.0006	0.0006	0.0008	0.0010	0.092
C_(95%)	0.0008	0.0006	0.0016	0.0004	0.0004	0.0005	0.0007	0.062

Note: C_(95%) is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Exova Ltd	Middlesbrough, UK	UKAS accreditation	0239
Sheffield Analytical Services	Sheffield, UK	UKAS accreditation	0012
AnchorCert Analytical	Birmingham, UK	UKAS accreditation	0667
Universal Scientific Laboratory Pty Ltd	Milperra, NSW, Australia	NATA accreditation	0492
Genitest Inc.	Montreal, QC, Canada	PRI accreditation	123077
Luo Yang Copper	Luo Yang, He Nan, China	CNAL accreditation	0173
Shandong Metallurgical & Science Research	Jinan, Shandong, China	CNAS accreditation	1461
Bureau Veritas CPS Ltd	Chennai, India	NABL accreditation	0025
TCR Engineering Services PVT. Ltd	Mumbai, India	NABL accreditation	0367
Raghavendra Spectro Metallurgical Laboratory	Bangalore, India	NABL accreditation	0371
Institute of Non-ferrous Metals	Gliwice, Poland	PCA accreditation	AB274
TEC Eurolab SRL	Modena, Italy	ACCREDIA accreditation	52
Mineral and Metallurgical Laboratories	Bangalore, India		
AMG Superalloys UK Ltd	Rotherham, UK		
Analyticka Laborator Lithea sro	Brno, Czech Republic		
Coleshill Laboratories Ltd	Coleshill, UK		

Note: to achieve the above accreditation (UKAS, etc), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT	RESULT No. & METHOD			
	ICP-AES	FAAS		OTHER
Tin	1-4, 6, 7, 10-13	5	8, 9	volumetric (iodine) photometric (phenyl fluorone)
Lead	3-5, 7, 9-11, 13, 14	1, 2, 6, 12	8	gravimetric
Zinc	1, 2, 5-7, 9-11, 13, 14	4, 8, 12	3, 15	volumetric (EDTA)
Iron	4-7, 10, 12, 13	1, 8	2, 3, 9, 11	volumetric (dichromate) photometric (orthophenanthroline)
Nickel	2, 5, 10-13	3	1, 6, 7, 9	gravimetric (dimethyl glyoxime)
Aluminium	1, 5, 7, 9, 11-13	4	4, 8	photometric (dimethyl glyoxime)
Manganese	1, 3, 6, 7, 9, 11	4, 10, 12	2, 3, 6, 8, 10	volumetric (EDTA) photometric (chrome azurol S)
Silicon	3, 5, 8, 11-14	-	2, 8	photometric (periodate)
Cobalt	1, 3, 4, 7, 8, 10, 11, 13-16	2, 5, 6, 9	5	volumetric (arsenite)
Arsenic	2, 4-14	3	1, 2, 4, 6, 7, 9, 10	gravimetric (perchloric acid) photometric (molybdenum blue)
Phosphorus	1, 4, 5, 7, 9, 11, 12	-	12	gravimetric (oxide)
Magnesium	1, 2, 4-9, 11, 12	3, 10	1	photometric (turbidity)
Chromium	1-3, 6-11, 13	4, 5, 12	2, 13	photometric (molybdenum blue)
Silver	2-5, 8, 10-12	1, 6, 7, 9	3, 6, 8, 10	volumetric (alkalimetric)
Tellurium	1-4, 7-10	6		
Copper	1, 3, 9	-	2, 4, 6	electrogravimetric
			5, 7, 8, 10, 11	volumetric (thiosulfate)

Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2015 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with this method of chill casting, have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face of the disc. Material to the rear of the disc, to a depth of ~3 mm, is not certified.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in December 2036, although we reserve the right to make changes as issue revisions, in the intervening period.

This material is also available in the form of chippings

The manufacture, analysis and certification of this product were supervised by C. Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.