



HOLLAND HOUSE • QUEENS ROAD • BARNET • EN5 4DJ • ENGLAND • TEL: +44 (0)20 8441 2024 • FAX: +44 (0)20 8449 0810 email: info@mbh.co.uk web: www.mbh.co.uk

# CERTIFICATE OF ANALYSIS

33X 54400 (batch A)

### **Certified Reference Material Information**

Type: GUN METAL (WROUGHT)

Form and Size: Disc ~38mm diameter

Manufactured by: Commercial Barstock

Certified and Supplied by: MBH Analytical Ltd

### **Assigned Values**

#### Percentage element by weight

Element	Sn	Pb	Zn	Fe	Ni	Al	As
Value <sup>1</sup>	3.97	4.69	3.87	0.072	0.244	0.0009	0.0156
Uncertainty <sup>2</sup>	0.03	0.03	0.04	0.002	0.002	0.0001	0.0005

Element	Р	Со	Sb	Ag	S	Cu
Value <sup>1</sup>	0.243	0.0013	0.0362	0.0124	0.0251	86.79
Uncertainty <sup>2</sup>	0.004	0.0001	0.0010	0.0005	0.0007	0.05

### **Definitions**

- The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

<u>Certified by:</u>		
MBH ANALYTICAL LIMITED_		on 28 <sup>th</sup> August 2014
	C Eveleigh	

## **Method of Preparation**

This reference material was produced from commercial barstock to UNS C54400. The metal was continuous cast, hot-rolled and cold-finished.

#### **Sampling**

Samples for chemical analysis were taken from various positions throughout the batch. Approximately 10% of all discs were selected for non-destructive homogeneity testing.

### **Homogeneity**

The discs were checked for sample and batch uniformity using an optical emission spectrometer.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

#### **Chemical Analysis**

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

#### **Estimation of Uncertainties**

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ( $C_{(95\%)}$ ) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, described above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

## **Traceability**

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

#### <u>Usage</u>

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use:

Copper alloys are generally prepared by machining on a mill or a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

## **Analytical Data**

#### Percentage element by weight

Sample	Sn	Pb	Zn	Fe	Ni	Al	As
1	3.896	4.638	3.778	0.0691	0.235	0.0006	0.0144
2	3.900	4.641	3.803	0.0693	0.236	0.0007	0.0145
3	3.917	4.656	3.819	0.0698	0.241	0.0007	0.0145
4	3.925	4.679	3.823	0.0710	0.241	0.0008	0.0149
5	3.926	4.681	3.831	0.0711	0.241	0.0008	0.0150
6	3.942	4.685	3.870	0.0717	0.243	0.0008	0.0150
7	3.946	4.692	3.881	0.0721	0.244	0.0010	0.0153
8	3.951	4.696	3.887	0.0736	0.244	0.0010	0.0155
9	3.995	4.706	3.915	0.0736	0.245	0.0010	0.0157
10	4.004	4.729	3.917	0.0741	0.245	0.0010	0.0158
11	4.007	4.732	3.944	0.0745	0.245	0.0010	0.0158
12	4.032	4.735	3.951	0.0755	0.246	0.0012	0.0161
13	4.034	4.747		0.0762	0.246		0.0163
14	4.036				0.249		0.0165
15					0.250		0.0169
16					0.252		0.0171
Mean	3.965	4.694	3.868	0.0724	0.244	0.0009	0.0156
Std Dev	0.051	0.036	0.057	0.0023	0.005	0.0002	0.0008
C <sub>(95%)</sub>	0.029	0.021	0.036	0.0014	0.002	0.0001	0.0005

Sample	Р	Co	Sb	Ag	S	Cu
1	0.233	0.0010	0.0333	0.0109	0.0232	86.70
2	0.234	0.0011	0.0347	0.0110	0.0237	86.73
3	0.236	0.0012	0.0348	0.0112	0.0242	86.79
4	0.237	0.0013	0.0349	0.0119	0.0243	86.80
5	0.238	0.0013	0.0358	0.0121	0.0245	86.80
6	0.242	0.0013	0.0359	0.0125	0.0245	86.81
7	0.245	0.0013	0.0360	0.0126	0.0248	86.82
8	0.245	0.0013	0.0370	0.0126	0.0260	86.82
9	0.245	0.0014	0.0373	0.0126	0.0260	86.86
10	0.248	0.0014	0.0374	0.0128	0.0261	
11	0.249	0.0014	0.0374	0.0129	0.0264	
12	0.251	0.0014	0.0378	0.0131	0.0265	
13	0.253	0.0015	0.0386	0.0135	0.0265	
14		0.0016		0.0141		
15		0.0017				
Mean	0.243	0.0013	0.0362	0.0124	0.0251	86.79
Std Dev	0.007	0.0002	0.0015	0.0009	0.0012	0.05
C <sub>(95%)</sub>	0.004	0.0001	0.0009	0.0005	0.0007	0.04

Note:  $C_{(95\%)}$  is the 95% half-width confidence interval derived from the equation:

 $C_{(95\%)} = (t \times SD)/\sqrt{n}$ 

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

#### **Participating Laboratories**

Exova Ltd Sheffield Assay Office Universal Scientific Laboratory Pty Ltd Laboratory Testing, Inc Shanghai Jinyi Test Tech Co Luo Yang Copper Shandong Metallurgical & Science Research Jinan, Shandong, China Bureau Veritas CPS Pvt Ltd Raghavendra Spectromet Laboratory TCR Engineering Services Ltd Institute of Non-Ferrous Metals Tec-Eurolab Colonial Metals Co

Milperra, NSW, Australia Hatfield, PA, USA Shanghai, China Luo Yang, He Nan, China Chennai, India Bangalore, India Mumbai, India Gliwice. Poland Campogalliano, Italy Columbia, PA, USA Rotherham, England Birmingham, England Brno, Czech Republic

Middlesbrough, England

Sheffield, England

UKAS accreditation 0239 UKAS accreditation 0012 NATA accreditation 0492 A2LA accreditation 0117 CNAS accreditation L0041 CNAL accreditation 0173 CNAS accreditation 1461 NABL accreditation 0025 NABL accreditation 0371 NABL accreditation 0367 PCA accreditation AB274 ACCREDIA accreditation 52

Note: to achieve the above accreditation (UKAS, NATA, etc.), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

#### Analytical Methods Used

London & Scandinavian Met. Co.

Coleshill Laboratories Ltd

Lithea sro

ELEMENT	RESULT No. & METHOD						
	ICP-AES	FAAS		OTHER			
Tin	2, 3, 6, 8-10, 12, 14	5	1, 11, 13	volumetric (iodate)			
			4	XRF			
			7	photometric (phenyl fluorone)			
Lead	1-4, 7, 10, 13	6, 8, 9	5	volumetric (EDTA)			
			11, 12	electrogravimetric			
Zinc	3-5, 8, 9, 11, 12	1, 6	2, 7	volumetric (EDTA)			
			10	XRF			
Iron	2-5, 7-9, 11, 13	1, 10, 12	6	photometric (orthophenanthroline)			
Nickel	1-3, 5-7, 10-12, 14, 16	8, 9, 13	4	XRF			
			15	photometric (dimethyl glyoxime)			
Aluminium	1, 3, 4, 5, 6, 8-12	2, 4, 7					
Arsenic	1-7, 9, 12-16	10, 11	8	photometric (turbidity)			
Phosphorus	1, 3, 4, 6-8, 11, 12	-	2, 5, 10	photometric (molybdenum yellow)			
			9, 13	volumetric (alkalimetric)			
Cobalt	2, 3, 6-8, 10-15	1, 4, 5, 9					
Antimony	2-5, 7, 8, 10, 11, 13	1, 6, 9	12	photometric (crystal violet)			
Silver	1, 3, 5, 6, 8-10, 12-14	2, 4, 7, 11		•			
Sulfur	1, 13	-	2-12	combustion with infra-red detection			
Copper	1, 8, 9	-	2, 6	volumetric (thiosulfate)			
			3-5, 7	electrogravimetric			

#### **Notes**

This Certified Reference Material has been produced and certified, wherever possible, in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2000 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

This certification is applicable to the whole of the disc. However, in accordance with normal practice for OES, it is appropriate to avoid usage of the central portion of approx 6mm diameter.

This material will remain stable provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in August 2034, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.