



HOLLAND HOUSE • QUEENS ROAD • BARNET • EN5 4DJ • ENGLAND • TEL: +44 (0)20 8441 2024 • FAX: +44 (0)20 8449 0810 email: info@mbh.co.uk web: www.mbh.co.uk

CERTIFICATE OF ANALYSIS

34X NS1 (batch F)

Certified Reference Material Information

Type: NICKEL SILVER (CHILL CAST)

Form and Size: Disc 42mm Diameter x 18mm Thickness

Manufactured by: Polycast Limited

Certified and Supplied by: MBH Analytical Limited

Certified Analysis

Percentage element by weight

Element	Sn	Pb	Zn	Fe	Ni	Со	Si	Mn
Value ¹	0.0110	0.0141	33.41	0.064	7.81	0.052	(0.002)	0.0009
Uncertainty 2	0.0009	0.0013	0.10	0.002	0.07	0.002	-	0.0002

Element	Cr	Al	Р	S	Mg	Ag	С	Cu
Value ¹	0.0003	(0.003)	0.0140	(0.0004)	0.0020	0.069	(0.0018)	58.63
Uncertainty 2	0.0001	-	0.0013	-	0.0004	0.002	_	0.10

Note: values given in parentheses are not certified - they are provided for information only.

Definitions

- The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

|--|

MBH ANALYTICAL LIMITED _		on 14th February 2005 –
	C Eveleigh	

Method of Preparation

This reference material was produced from commercial-purity metals, and master alloys. The discs are the product of one melt poured into a sequence of multiple chill moulds with feeding systems designed to ensure sound discs. Metal was removed from the cast faces of the discs to minimise surface effects.

Sampling

Samples for chemical analysis were taken from various positions throughout the casting process. Approximately 10% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

The discs were checked for sample and batch uniformity using an optical emission spectrometer. One disc was checked for vertical uniformity using the same method.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2000, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, described above.

The final certified uncertainty for each element has been derived by combining these two factors, using the squareroot of the summed squares.

Traceability

Most of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to a national authority. It is part of the requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised primary reference materials.

<u>Usage</u>

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use:

Copper alloys are generally prepared by machining on a mill or a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

			Percentag	e element by	/ weight			
Sample	Sn	Pb	Zn	Fe	Ni	Co	Si	Mn
1	0.0088	0.0123	33.25	0.0610	7.67	0.0486	0.0010	0.0006
2	0.0098	0.0125	33.27	0.0610	7.724	0.0489	0.0010	0.0008
3	0.0100	0.0133	33.35	0.0618	7.738	0.0490	0.0015	0.0008
4	0.0104	0.0135	33.44	0.0639	7.74	0.0501	0.0019	0.0010
5	0.0108	0.0147	33.46	0.0646	7.78	0.0510	0.0033	0.0010
6	0.0109	0.0148	33.47	0.065	7.80	0.0531	0.0034	0.0010
7	0.0118	0.0159	33.50	0.0653	7.83	0.0542	<0.005	0.0011
8	0.012	0.0163	33.50	0.0657	7.85	0.0544		
9	0.0121			0.0680	7.895	0.0549		
10	0.0123				7.92			
11	0.0126				7.935			
Mean	0.0110	0.0141	33.41	0.0640	7.807	0.0516	(0.0020)	0.0009
Std Dev	0.0012	0.0015	0.10	0.0024	0.087	0.0026	-	0.0002
C _(95%)	0.0008	0.0013	0.08	0.0018	0.058	0.0020	-	0.0002
Sample	Cr	Al	Р	S	Mg	Ag	С	Cu
1	0.0001	0.0006	0.0119	0.00014	0.0013	0.0632	0.0010	58.47
2	0.0002	0.0011	0.012	0.0004	0.0015	0.0655	0.0013	58.61
3	0.0002	0.0020	0.0128	0.0006	0.0019	0.0684	0.0014	58.62
4	0.0003	0.0022	0.0130	0.0006	0.0019	0.0686	0.0015	58.65
5	0.0003	0.0023	0.0134	<0.001	0.0021	0.0694	0.0018	58.68
6	0.0003	0.0040	0.0139	<0.001	0.0023	0.0696	0.0025	58.68
7	0.0005	0.0048	0.0139	<0.001	0.0023	0.0698	0.0031	58.71
8	<0.001	0.0051	0.0153	<0.002	0.0028	0.0714		
9	<0.001		0.0165			0.0717		
10			0.0174					
Mean	0.0003	(0.0028)	0.0140	(0.0004)	0.0020	0.0686	(0.0018)	58.63
Std Dev	0.0001	-	0.0018	-	0.0005	0.0027	-	0.08
C _(95%)	0.0001	-	0.0013	-	0.0004	0.0021	-	0.07

Note: $C_{(95\%)}$ is the 95% half-width confidence interval derived from the equation:

 $C_{(95\%)} = (t \times SD)/\sqrt{n}$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Bodycote Materials Testing
Sheffield Assay Office
Laboratory Testing Inc
Universal Scientific Laboratory Pty Ltd
Central Iron & Steel Research Inst
Institute of Iron & Steel Technology
Luo Yang Copper
RWTUV Laboratory
Spectroscopic Solutions Ltd
Genitest Inc
Coleshill Laboratories Ltd

Middlesbrough, England Sheffield, England Hatfield, PA, USA Milperra, NSW, Australia Beijing, China Shanghai, China Luo Yang, He Nan, China Brno, Czech Republic Johannesburg, South Africa Montreal, Canada Coleshill, England UKAS accreditation 0239 UKAS accreditation 0012 A2LA accreditation 0117 NATA accreditation 492 CNAL accreditation 0435 CNAL accreditation 0783 CNAL accreditation 0173 CAI accreditation 1060

Note: to achieve National Accreditation (eg UKAS, NATA, A2LA, CNAL, CAI), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT	RESULT No. & METHOD						
	ICP-AES	FAAS		OTHER			
Tin	2-4, 6-11	1	5	volumetric (iodate)			
Lead	2-5, 7, 8	1	6	volumetric (sulfuric acid, EDTA)			
Zinc	2, 5-7	3	1, 4, 8	volumetric (EDTA)			
Iron	2-5, 7-9	6	1	photometric (orthophenanthroline)			
Nickel	2-4, 7-10	5	1	volumetric (dimethyl glyoxime/EDTA)			
			6	gravimetric (dimethyl glyoxime)			
			11	photometric (dimethyl glyoxime)			
Cobalt	1, 2, 4, 6-9	3, 5					
Silicon	2, 3, 5-7	-	1, 4	photometric (molybdenum blue)			
Manganese	1-3, 5-7	4					
Chromium	2-9	1					
Aluminium	1, 3-8	2					
Phosphorus	1, 3-5, 8, 10	-	2, 6, 7, 9	photometric (molybdenum yellow)			
Sulfur	4	-	1, 2, 5-8	combustion (infra-red detection)			
			3	combustion (volumetric detection)			
Magnesium	1, 4-8	2, 3					
Silver	1, 2, 5, 6, 8, 9	4, 7	3	ICP-MS			
Carbon	-	-	all	combustion (infra-red detection)			
Copper	1, 4	-	2, 6	volumetric (thiosulfate)			
			5, 7	electrogravimetric			
			3	photometric (BCO)			

Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2000, ISO Guide 31-2000 and ISO Guide 35-1989, taking into account the requirements of ASTM E1724, ASTM E1831 and the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with chill casting may have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face of the disc to a depth of ~13mm. Material to the rear of the disc, to a depth of ~5mm, is not certified.

This material will remain stable provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. This certification will therefore expire in February 2025, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.