

CERTIFICATE OF ANALYSIS

36X CCR1 (batch E)

Certified Reference Material Information

Type: COPPER / CHROMIUM / ZIRCONIUM (WROUGHT)
Form and Size: Disc 50mm diameter
Manufactured by: KM Europa Metal AG, Germany
Certified and Supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

Element	Sn	Pb	Zn	Fe	Ni	Al	P
Value ¹	0.0018	0.0008	0.0009	0.0170	0.0111	0.0013	0.0223
Uncertainty ²	0.0002	0.0002	0.0002	0.0011	0.0008	0.0003	0.0008

Element	As	Zr	Cr	Mg	Ag	S	Cu
Value ¹	0.0007	0.079	0.652	(0.0003)	0.0042	0.0015	99.24
Uncertainty ²	0.0002	0.003	0.005	-	0.0008	0.0002	0.05

Note: values given in parentheses are not certified - they are provided for information only.

Definitions

- ¹ The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- ² The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:

MBH ANALYTICAL LIMITED _____

on 15th December 2014

C Eveleigh



Method of Preparation

This reference material was produced from commercial barstock. The detailed metallurgical history of this material is unknown.

Sampling

Samples for chemical analysis were taken from various positions throughout the bar. Approximately 7% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

The discs were checked for sample and batch uniformity using an optical emission spectrometer.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, described above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Copper alloys are generally prepared by machining on a mill or a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

Sample	Sn	Pb	Zn	Fe	Ni	Al	P
1	0.0013	0.0003	0.0005	0.0143	0.0102	0.0007	0.0209
2	0.0014	0.0005	0.0007	0.0148	0.0104	0.0007	0.0212
3	0.0015	0.0006	0.0008	0.0152	0.0109	0.0009	0.0213
4	0.0017	0.0007	0.0009	0.0153	0.0112	0.0009	0.0217
5	0.0017	0.0009	0.0010	0.0154	0.0115	0.0010	0.0223
6	0.0017	0.0010	0.0011	0.0161	0.0116	0.0010	0.0223
7	0.0018	0.0010	0.0011	0.0172	0.0121	0.0010	0.0225
8	0.0018	0.0010	0.0012	0.0173		0.0012	0.0232
9	0.0019	0.0011		0.0177		0.0013	0.0235
10	0.0019	0.0011		0.0179		0.0013	0.0243
11	0.0019			0.0187		0.0017	
12	0.0020			0.0188		0.0018	
13	0.0023			0.0194		0.0019	
14				0.0201		0.0022	
Mean	0.0018	0.0008	0.0009	0.0170	0.0111	0.0013	0.0223
Std Dev	0.0003	0.0003	0.0002	0.0019	0.0007	0.0005	0.0011
C_(95%)	0.0002	0.0002	0.0002	0.0011	0.0007	0.0003	0.0008

Sample	As	Zr	Cr	Mg	Ag	S	Cu
1	0.0003	0.0742	0.638	0.00004	0.0031	0.0010	99.16
2	0.0005	0.0748	0.639	0.00004	0.0033	0.0012	99.17
3	0.0005	0.0752	0.644	0.00005	0.0035	0.0013	99.20
4	0.0006	0.0769	0.649	0.00010	0.0041	0.0013	99.21
5	0.0006	0.0776	0.654	0.00036	0.0042	0.0014	99.21
6	0.0007	0.0803	0.655	0.00040	0.0045	0.0015	99.27
7	0.0007	0.0803	0.657	0.00040	0.0051	0.0016	99.28
8	0.0009	0.0805	0.658	0.00050	0.0058	0.0016	99.32
9	0.0009	0.0807	0.658	0.00060		0.0018	99.34
10	0.0009	0.0816	0.658			0.0019	
11	0.0011	0.0843	0.659			0.0019	
12						0.0020	
Mean	0.0007	0.0788	0.652	(0.0003)	0.0042	0.0015	99.24
Std Dev	0.0002	0.0032	0.008	-	0.0009	0.0003	0.06
C_(95%)	0.0001	0.0022	0.005	-	0.0008	0.0002	0.05

Note: $C_{(95\%)}$ is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Exova Ltd	Middlesbrough, England	UKAS accreditation 0239
Sheffield Assay Office	Sheffield, England	UKAS accreditation 0012
Birmingham Assay Office	Birmingham, England	UKAS accreditation 0667
Universal Scientific Laboratory Pty Ltd	Milperra, NSW, Australia	NATA accreditation 0492
Genitest, Inc	Montreal, Canada	PRI accreditation 123077
Shandong Metallurgical & Science Research	Jinan, Shandong, China	CNAS accreditation 1461
Bureau Veritas CPS Pvt Ltd	Chennai, India	NABL accreditation 0025
Raghavendra Spectromet Laboratory	Bangalore, India	NABL accreditation 0371
TCR Engineering Services Ltd	Mumbai, India	NABL accreditation 0367
Institute of Non-Ferrous Metals	Gliwice, Poland	PCA accreditation AB274
Tec-Eurolab	Campogalliano, Italy	ACCREDIA accreditation 52
Colonial Metals Co	Columbia, PA, USA	
London & Scandinavian Met. Co	Rotherham, England	
Coleshill Laboratories Ltd	Birmingham, England	
Lithea sro	Brno, Czech Republic	

Note: to achieve the above accreditation (UKAS, NATA, etc), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT	RESULT No. & METHOD		
	ICP-AES	FAAS	OTHER
Tin	1-3, 5-10, 13	4, 11, 12	
Lead	1, 3-5, 8-10	2, 6	7 volumetric (EDTA)
Zinc	1-4, 6, 7	5	8 volumetric (EDTA)
Iron	1-3, 6-11, 13, 14	4, 5, 12	
Nickel	1-3, 6, 7	4	5 volumetric (dimethyl glyoxime)
Aluminium	2-8, 10-12, 14	1, 9, 13	
Phosphorus	1-4, 6, 7, 9, 10	-	5 photometric (molybdenum yellow) 8 volumetric (alkalimetric)
Arsenic	1, 3-9, 11	2, 10	
Zirconium	1-5, 8-11	6, 7	
Chromium	1, 3-6, 8, 9, 11	2, 10	7 XRF
Magnesium	2-7, 9	1, 8	
Silver	1, 2, 5-8	3, 4	
Sulfur	2-5, 11	-	1, 6-10, 12 combustion (IR detection)
Copper	2, 8, 9	-	1, 5-7 electrogravimetric 3, 4 volumetric (thiosulfate)

Notes

This Certified Reference Material has been tested and certified, wherever possible, in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2000 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

This certification is applicable to the whole of the disc. However, in accordance with normal practice for emission spectrometry, it is appropriate to avoid usage of the centre of the disc, ~8 mm diameter.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in December 2034, although we reserve the right to make changes as issue revisions, in the intervening period.

This material is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.