

CERTIFICATE OF ANALYSIS

36X CN22 (batch A)

Certified Reference Material Information

Type: COINAGE ALLOY (CHILL CAST)
Form and Size: Disc 40mm Diameter x 17mm Thickness
Manufactured by: Polycast Limited
Certified and Supplied by: MBH Analytical Limited

Assigned Values

Percentage element by weight

Element	Cu	Ni	Al	Zn	Sn	Pb	Fe
Value ¹	91.80	1.806	6.09	0.0175	0.0371	0.0260	0.088
Uncertainty ²	0.08	0.017	0.04	0.0005	0.0011	0.0015	0.003

Element	Mn	Co	P	As	Ag	Cr	Cd
Value ¹	(0.016)	0.0231	0.0178	0.0206	0.0196	0.0144	0.0083
Uncertainty ²	-	0.0007	0.0008	0.0013	0.0010	0.0007	0.0003

Note: values given in parentheses are not certified - they are provided for information only.

Definitions

- ¹ The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- ² The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:

MBH ANALYTICAL LIMITED _____ on 25th June 2007
C Eveleigh

Method of Preparation

This reference material was produced from commercial-purity metals, and master alloys. The discs are the product of one melt poured into a sequence of multiple chill moulds with feeding systems designed to ensure sound discs. Metal was removed from the cast faces of the discs to minimise surface effects.

Sampling

Samples for chemical analysis were taken from various positions throughout the casting process. At least 15% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

The discs were checked for sample and batch uniformity using an optical emission spectrometer. One disc was checked for vertical uniformity using the same method.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2000, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Most of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to a national authority. It is part of the requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised primary reference materials.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Copper alloys are generally prepared by machining on a mill or a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

Sample	Cu	Ni	Al	Zn	Sn	Pb	Fe
1	91.70	1.749	6.010	0.0162	0.0347	0.0225	0.0841
2	91.71	1.774	6.018	0.0170	0.0359	0.0232	0.0842
3	91.71	1.798	6.056	0.0171	0.0367	0.0254	0.0842
4	91.79	1.808	6.097	0.0173	0.0370	0.0255	0.0859
5	91.83	1.812	6.112	0.0174	0.0371	0.0260	0.0884
6	91.87	1.813	6.112	0.0175	0.0372	0.0260	0.0888
7	91.88	1.815	6.120	0.0176	0.0375	0.0262	0.0895
8	91.93	1.819	6.124	0.0179	0.0378	0.0266	0.0897
9		1.821	6.137	0.0181	0.0400	0.0271	0.0940
10		1.827	6.140	0.0191		0.0281	0.0961
11		1.830				0.0297	
Mean	91.80	1.806	6.093	0.0175	0.0371	0.0260	0.0884
Std Dev	0.09	0.024	0.048	0.0008	0.0014	0.0020	0.0041
C_(95%)	0.07	0.016	0.034	0.0005	0.0011	0.0014	0.0030

Sample	Mn	Co	P	As	Ag	Cr	Cd
1	0.0132	0.0211	0.0163	0.0183	0.0178	0.0129	0.0074
2	0.0144	0.0217	0.0168	0.0186	0.0186	0.0135	0.0079
3	0.0148	0.0218	0.0170	0.0190	0.0187	0.0136	0.0080
4	0.0159	0.0223	0.0173	0.0192	0.0187	0.0136	0.0080
5	0.0159	0.0227	0.0173	0.0201	0.0188	0.0138	0.0082
6	0.0169	0.0229	0.0176	0.0204	0.0189	0.0140	0.0083
7	0.0170	0.0231	0.0182	0.0213	0.0196	0.0142	0.0084
8	0.0177	0.0232	0.0186	0.0217	0.0201	0.0150	0.0084
9	0.0179	0.0240	0.0195	0.0226	0.0202	0.0155	0.0086
10	0.0179	0.0240	0.0196	0.0228	0.0218	0.0158	0.0086
11	0.0188	0.0241		0.0230	0.0226	0.0161	0.0087
12		0.0248					0.0090
13		0.0252					
Mean	0.0164	0.0231	0.0178	0.0206	0.0196	0.0144	0.0083
Std Dev	0.0017	0.0012	0.0011	0.0017	0.0015	0.0011	0.0004
C_(95%)	0.0012	0.0007	0.0008	0.0012	0.0010	0.0007	0.0003

Note: C_(95%) is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Bodycote Materials Testing
Sheffield Assay Office
Universal Scientific Laboratory Pty Ltd
Laboratory Testing, Inc
Institute of Iron & Steel Technology
Luo Yang Copper
Institute of Non-Ferrous Metals
Sargam Metals Pvt Ltd
TCR Engineering Services Ltd
Molybdenos y Metales SA
De Bruyn Spectroscopic Solutions Ltd
London & Scandinavian Met co Ltd
Coleshill Laboratories Ltd

Middlesbrough, England
Sheffield, England
Milperra, NSW, Australia
Hatfield, PA, USA
Shanghai, China
Luo Yang, He Nan, China
Gliwice, Poland
Chennai, India
Mumbai, India
San Bernardo, Santiago, Chile
Johannesburg, South Africa
Rotherham, England
Coleshill, England

UKAS accreditation 0239
UKAS accreditation 0012
NATA accreditation 492
A2LA accreditation 0117
CNAL accreditation 0783
CNAL accreditation 0173
PCA accreditation AB274
NABL accreditation 0025
NABL accreditation 0367

Note: to achieve National Accreditation (eg UKAS, NATA, A2LA, CNAL, PCA, NABL), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT	RESULT No. & METHOD				
	ICP-AES	XRF	FAAS	OTHER	
Copper	3	6	-	2, 4 1, 5, 7, 8	volumetric (thiosulfate) electrogravimetric
Nickel	2-4, 8, 9	1	6, 11	10 5, 7	gravimetric (dimethyl glyoxime) volumetric (dimethyl glyoxime)
Aluminium	2, 3, 6, 8-10	4	5	1 7	photometric (chrome azurol-S) volumetric (EDTA)
Zinc	1-5	-	6-10		
Tin	1-3, 6, 8, 9	-	4, 7	5	photometric (phenyl fluorone)
Lead	5-9, 11	2	1, 3, 4, 10		
Iron	1, 4, 6, 8, 9	-	2, 3, 5, 7, 10		
Manganese	1-4, 6, 7, 9	8	5, 10, 11		
Cobalt	1, 3, 5-8, 12	-	2, 4, 9-11, 13		
Phosphorus	1-6	8	-	7, 10 9	photometric (molybdenum yellow) volumetric (alkalimetric)
Arsenic	1, 3, 5, 8-11	7	2, 4	6	photometric (molybdenum yellow)
Silver	1-5, 7, 9	-	6, 8, 10, 11		
Chromium	1-5, 7, 9	-	6, 8, 10, 11		
Cadmium	2-5, 8, 10	-	1, 7, 9, 11, 12	6	ICP-MS

Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2000, ISO Guide 31-2000 and ISO Guide 35-1989, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with chill casting have led to the formation of inhomogeneous segregates in the rear portion of the disc. However, testing has shown that the above certification is applicable from the front face of the disc to a depth of 12mm. Material to the rear of the disc, to a depth of ~5mm, is not certified.

This material will remain stable provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. This certification will therefore expire in June 2027, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.