

CERTIFICATE OF ANALYSIS

36X CN7 (batch F)

Certified Reference Material Information

Type: CUPRO-NICKEL (CHILL CAST)
Form and Size: Disc 40mm Diameter x 17mm Thickness
Produced by: Polycast Limited
Certified and supplied by: MBH Analytical Limited

Assigned Values

Percentage element by weight

Element	Sn	Pb	Zn	Fe	Ni	Co	Si	Mn	Cr	Mg
Value ¹	0.039	0.028	0.203	1.021	29.95	0.108	0.304	0.659	1.51	0.0041
Uncertainty ²	0.002	0.004	0.006	0.014	0.14	0.002	0.008	0.014	0.02	0.0005

Element	Nb	P	S	C	B	Zr	Ti	Bi	Cd	Cu
Value ¹	0.58	(0.021)	0.0151	0.0106	(0.004)	(0.003)	(0.037)	(0.014)	0.0024	65.58
Uncertainty ²	0.02	-	0.0007	0.0011	-	-	-	-	0.0003	0.08

Note: values given in parentheses are not certified - they are provided for information only.

Definitions

- ¹ The assigned values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- ² The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:

MBH ANALYTICAL LIMITED _____

on 28th June 2006

C Eveleigh

Method of Preparation

This reference material was produced from commercial-purity metals, and master alloys. The discs are the product of one melt poured into a sequence of multiple chill moulds with feeding systems designed to ensure sound discs. Metal was removed from the cast faces of the discs to minimise surface effects.

Sampling

Samples for chemical analysis were taken from various positions throughout the casting process. At least 15% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

The discs were checked for sample and batch uniformity using an optical emission spectrometer. One disc was checked for vertical uniformity using the same method.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2000, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Most of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to a national authority. It is part of the requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised primary reference materials.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Cupro-nickels are generally prepared by finishing, turning or milling. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

Sample	Sn	Pb	Zn	Fe	Ni	Co	Si	Mn	Cr	Mg
1	0.0336	0.0209	0.190	1.000	29.66	0.103	0.290	0.624	1.452	0.0030
2	0.0351	0.0225	0.190	1.002	29.68	0.104	0.291	0.630	1.470	0.0034
3	0.0374	0.0229	0.193	1.008	29.80	0.104	0.298	0.631	1.499	0.0036
4	0.0380	0.025	0.197	1.010	29.90	0.104	0.300	0.640	1.499	0.0037
5	0.0382	0.0300	0.202	1.010	29.91	0.107	0.301	0.647	1.500	0.0040
6	0.0382	0.0302	0.202	1.014	29.92	0.108	0.301	0.654	1.506	0.004
7	0.0402	0.0307	0.203	1.016	29.95	0.110	0.307	0.658	1.508	0.0042
8	0.0405	0.0336	0.208	1.020	30.06	0.110	0.316	0.664	1.517	0.0042
9	0.0409	0.0337	0.210	1.022	30.11	0.110	0.318	0.679	1.52	0.0042
10	0.041	0.0339	0.211	1.025	30.24	0.110	0.321	0.680	1.520	0.0045
11	0.041		0.213	1.040	30.26	0.111		0.684	1.534	0.0045
12			0.214	1.044		0.114		0.688	1.54	0.0060
13				1.066				0.690	1.545	
Mean	0.0386	0.0283	0.203	1.021	29.95	0.108	0.304	0.659	1.508	0.0041
Std Dev	0.0025	0.0050	0.009	0.019	0.20	0.004	0.011	0.024	0.026	0.0007
C_(95%)	0.0017	0.0036	0.006	0.011	0.13	0.002	0.008	0.014	0.016	0.0005

Sample	Nb	P	S	C	B	Zr	Ti	Bi	Cd	Cu
1	0.538	0.0142	0.0135	0.0084	0.0025	0.0017	0.0249	0.0096	0.0018	65.44
2	0.541	0.0145	0.0141	0.0090	0.0030	0.0018	0.0276	0.0105	0.0020	65.52
3	0.553	0.0151	0.0142	0.0091	0.0031	0.0019	0.0308	0.0115	0.0020	65.58
4	0.565	0.0205	0.0142	0.0100	0.0034	0.0022	0.0343	0.0122	0.0022	65.58
5	0.587	0.0205	0.0150	0.0100	0.0045	0.0027	0.0358	0.0128	0.0022	65.60
6	0.588	0.0225	0.0151	0.0107	0.0053	0.0038	0.0376	0.0132	0.0025	65.61
7	0.588	0.0229	0.0154	0.0111	0.0053	0.0038	0.0399	0.0137	0.0025	65.65
8	0.590	0.0230	0.0159	0.0120	0.0055	0.0050	0.0435	0.0146	0.0029	65.68
9	0.592	0.0244	0.0160	0.0123	0.0060		0.0446	0.0167	0.0029	
10	0.618	0.0282	0.0162	0.0132	0.0064		0.0451	0.0175	0.0030	
11	0.630	0.0290	0.0164				0.0470	0.0181		
Mean	0.581	0.0213	0.0151	0.0106	0.0045	0.0029	0.0374	0.0137	0.0024	65.58
Std Dev	0.029	0.0051	0.0010	0.0016	0.0014	0.0012	0.0074	0.0028	0.0004	0.07
C_(95%)	0.020	0.0035	0.0007	0.0011	0.0010	0.0010	0.0050	0.0019	0.0003	0.06

Note: $C_{(95\%)}$ is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

ATI Allvac Ltd	Sheffield, England	UKAS accreditation 0638
Bodycote Materials Testing Ltd	Middlesbrough, England	UKAS accreditation 0239
Sheffield Assay Office	Sheffield, England	UKAS accreditation 0012
IncoTest Ltd	Hereford, England	UKAS accreditation 0281
Universal Scientific Laboratory Pty Ltd	Milperra, NSW, Australia	NATA accreditation 0492
Institute of Iron & Steel Technology	Shanghai, China	CNAL accreditation 0783
Luo Yang Copper Co	Luo Yang, He Nan, China	CNAL accreditation 0173
TCR Engineering Services Ltd	Mumbai, India	NABL accreditation 0367
Sargam Metals Pvt Ltd	Chennai, India	NABL accreditation 0025
De Bruyn Spectroscopic Solutions	Johannesburg, South Africa	
Genitest Inc	Montreal, Canada	
Coleshill Laboratories Ltd	Coleshill, England	

Note: to achieve National Accreditation (eg UKAS, NATA, CNAL, NABL), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT	RESULT No. & METHOD		
	ICP-AES	FAAS	OTHER
Tin	2-4, 6, 7, 10, 11	1, 5	8, 9 photometric (phenyl fluorone)
Lead	1, 3-5, 7, 9, 10	2, 6, 8	
Zinc	2-7, 9, 11	1, 8, 10, 12	
Iron	2, 3, 5, 6, 9, 11, 13	1, 8, 12	4, 7, 10 volumetric (dichromate)
Nickel	3, 4, 8, 11	-	1, 2 volumetric (EDTA/dimethyl glyoxime)
			5, 6, 9, 10 gravimetric (dimethyl glyoxime)
			7 photometric (dimethyl glyoxime)
Cobalt	1, 3, 4, 8-12	2, 5, 6, 7	
Silicon	4, 5, 9, 10		1, 3 gravimetric (perchloric acid)
			2, 6, 7, 8 photometric (molybdenum blue)
Manganese	1-4, 6, 7, 9	8, 10, 11, 13	5, 12 photometric (periodate)
Chromium	2-4, 6, 8, 11-13	1, 7, 9	5, 10 volumetric (ferrous ammonium sulfate)
Magnesium	1-6, 10, 12	7, 8, 11	9 ICP-MS
Niobium	1-9	-	11 photometric (4-p.a.r.); 10: ICP-MS
Phosphorus	2, 5, 6, 10, 11	-	1, 7, 8, 9 photometric (molybdenum blue)
			3, 4 volumetric (alkalimetry)
Sulfur	1	-	2-7, 9-11 combustion (infra-red detection)
			8 combustion (volumetric detection)
Carbon	-	-	1, 3-10 combustion (infra-red detection)
			2 combustion (volumetric detection)
Boron	1-9	-	10 ICP-MS
Zirconium	1-5, 7	-	6 ICP-MS
Titanium	1, 3, 6-9, 11	2, 4	10 photometric (peroxide); 5: ICP-MS
Bismuth	1, 2, 5, 7, 9, 10	3, 6, 11	8 photometric (iodide); 4: ICP-MS
Cadmium	2-5, 7, 10	6, 8, 9	1 ICP-MS
Copper	3	-	1, 5, 7, 8 electrogravimetric
			2, 4, 6 volumetric (thiosulfate)

Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2000, ISO Guide 31-2000 and ISO Guide 35-1989, taking into account the requirements of ASTM E1724 and the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with chill casting, have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face of the disc, to a depth of 10mm. Material to the rear of the disc, to a depth of ~7mm, is not certified.

This material will remain stable provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. This certification will therefore expire in June 2006, although we reserve the right to make changes as issue revisions, in the intervening period. This sample is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd. The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.