

# CERTIFICATE OF ANALYSIS

**41X GLV2 (batch B)**

## Certified Reference Material Information

Type: ZINC GALVANIZING ALLOY (CAST)  
Form and Size: Disc ~50mm diameter  
Produced by: MBH Analytical Ltd  
Certified and supplied by: MBH Analytical Ltd

## Assigned Values

### Percentage element by weight

Element	Pb	Mg	Al	Cd	Fe	Sn	Co
Value <sup>1</sup>	<b>0.259</b>	<b>0.0006</b>	<b>0.111</b>	<b>0.0037</b>	<b>0.143</b>	<b>0.0148</b>	<b>0.0024</b>
Uncertainty <sup>2</sup>	0.005	0.0001	0.003	0.0002	0.008	0.0006	0.0001

Element	Ni	Cu	Bi	Sb	As	Cr	Mn
Value <sup>1</sup>	<b>0.0145</b>	<b>0.0050</b>	<b>0.0172</b>	<b>0.0071</b>	<b>0.0035</b>	<b>0.014</b>	<b>(0.033)</b>
Uncertainty <sup>2</sup>	0.0002	0.0003	0.0003	0.0002	0.0002	0.001	-

Note: values given in parentheses are not certified - they are provided for information only.

## Definitions

- <sup>1</sup> The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- <sup>2</sup> The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

## Certified by:

MBH ANALYTICAL LIMITED \_\_\_\_\_

on 31st October 2013

C Eveleigh



## **Method of Preparation**

This certified reference material was produced from commercial zinc, with the major alloys and traces added as pure elements or master alloys. The metal was cast from the bulk melt by sequential transfer of aliquots into individual iron chill moulds. At least 1mm has been machined from the working face of each disc, to minimise surface effects.

## **Sampling**

Samples for chemical analysis were taken from throughout the casting process. In addition, at least 10% of all discs, chosen at random from the complete batch, were selected for non-destructive homogeneity testing.

## **Homogeneity**

The discs were checked for sample and batch uniformity using an optical emission spectrometer.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

## **Chemical Analysis**

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

## **Estimation of Uncertainties**

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ( $C_{(95\%)}$ ) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

## **Traceability**

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

## **Usage**

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Zinc and zinc alloys are generally prepared by machining on a mill or lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

For OES the sample should be of sufficient mass to prevent excess heating during sparking, and the discharge chamber should be regularly cleaned as directed by the instrument manufacturer.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

## Analytical Data

### Percentage element by weight

Sample	Pb	Mg	Al	Cd	Fe	Sn	Co
1	0.246	0.0005	0.1060	0.0033	0.133	0.0132	0.0020
2	0.247	0.0005	0.1080	0.0034	0.134	0.0134	0.0021
3	0.249	0.00057	0.1080	0.0035	0.134	0.0134	0.0022
4	0.253	0.0006	0.1091	0.00351	0.136	0.0136	0.0022
5	0.254	0.0006	0.1100	0.00354	0.137	0.0140	0.0022
6	0.254	0.0006	0.1109	0.00356	0.141	0.0141	0.0023
7	0.255	0.0006	0.1110	0.0036	0.142	0.0146	0.0023
8	0.257	0.00062	0.1118	0.0036	0.142	0.0146	0.0024
9	0.257	0.00062	0.1120	0.00362	0.143	0.0151	0.0024
10	0.261	0.00064	0.1120	0.0037	0.144	0.0152	0.0024
11	0.262	0.0007	0.1130	0.00377	0.145	0.0152	0.0024
12	0.264	0.0007	0.1134	0.0038	0.145	0.0154	0.0024
13	0.265	0.0007	0.1145	0.0038	0.146	0.0159	0.0025
14	0.265	0.0008	0.1146	0.0038	0.150	0.0159	0.0026
15	0.267		0.1172	0.00396	0.154	0.0166	0.0028
16	0.272			0.0040	0.156	0.0168	0.0029
17	0.272						
<b>Mean</b>	<b>0.259</b>	<b>0.00063</b>	<b>0.1114</b>	<b>0.00365</b>	<b>0.143</b>	<b>0.0148</b>	<b>0.0024</b>
<b>Std Dev</b>	0.008	0.00008	0.0029	0.00019	0.007	0.0011	0.0002
<b>C<sub>(95%)</sub></b>	0.004	0.00005	0.0016	0.00010	0.004	0.0006	0.0001

Sample	Ni	Cu	Bi	Sb	As	Cr	Mn
1	0.0140	0.0044	0.0166	0.0065	0.0030	0.0132	0.0284
2	0.0140	0.0048	0.0166	0.0067	0.0030	0.0136	0.0286
3	0.0142	0.0048	0.0168	0.0067	0.0032	0.0137	0.0329
4	0.0142	0.0048	0.0169	0.0070	0.0034	0.0144	0.0347
5	0.0144	0.0049	0.0169	0.0071	0.0035	0.0148	0.0362
6	0.0145	0.0050	0.0171	0.0071	0.0036		0.0367
7	0.0146	0.0050	0.0171	0.0071	0.0036		
8	0.0146	0.0050	0.0173	0.0072	0.0036		
9	0.0147	0.0050	0.0174	0.0072	0.0036		
10	0.0148	0.0051	0.0175	0.0073	0.0036		
11	0.0148	0.0051	0.0175	0.0073	0.0036		
12	0.0150	0.0052	0.0179	0.0076	0.0038		
13	0.0153	0.0053	0.0186	0.0077			
14		0.0054					
<b>Mean</b>	<b>0.0145</b>	<b>0.0050</b>	<b>0.0172</b>	<b>0.0071</b>	<b>0.0035</b>	<b>0.0139</b>	<b>0.0329</b>
<b>Std Dev</b>	0.0004	0.0002	0.0006	0.0003	0.0003	0.0006	0.0037
<b>C<sub>(95%)</sub></b>	0.0002	0.0001	0.0003	0.0002	0.0002	0.0008	0.0038

Note: C<sub>(95%)</sub> is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

## Participating Laboratories

Exova Ltd  
Sheffield Assay Office  
Universal Scientific Laboratory Pty Ltd  
Luo Yang Copper  
Institute of Iron & Steel Technology  
South-West Aluminium Group  
TCR Engineering Services Ltd  
Sargam Laboratory Pvt Ltd  
Institute of Non-Ferrous Metals  
Tec-Eurolab  
London & Scandinavian Met Co  
Coleshill Laboratories Ltd  
Nyrstar Hobart Pty Ltd  
Sun Metals Corp  
Votorantim Metais  
Lithea sro

Middlesbrough, England  
Sheffield, England  
Milperra, NSW, Australia  
Luo Yang, He Nan, China  
Shanghai, China  
Jiulong Puo, Sichuan, China  
Mumbai, India  
Chennai, India  
Gliwice, Poland  
Campogalliano, Italy  
Rotherham, England  
Birmingham, England  
Hobart, Tas, Australia  
Townsville, Qld, Australia  
Lima, Peru  
Brno, Czech Republic

UKAS accreditation 0239  
UKAS accreditation 0012  
NATA accreditation 492  
CNAL accreditation 0173  
CNAL accreditation 0783  
CNAL accreditation T007  
NABL accreditation 0367  
NABL accreditation 0025  
PCA accreditation AB274  
ACCREDIA accreditation 52

Note: to achieve the above accreditation (eg UKAS, NATA, etc), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

## Analytical Methods Used

ELEMENT	RESULT No. & METHOD		
	ICP-AES	FAAS	OTHER
Lead	1, 2, 4-6, 8, 10, 12-17	3, 7, 9, 11	
Magnesium	1-3, 5-7, 9-11, 13, 14	4, 8, 12	
Aluminium	1, 3, 5, 7, 8, 10-15	2, 6	4 photometric (chrome azurol S) 9 volumetric (EDTA)
Cadmium	1-3, 5-7, 10-12, 14-16	4, 8, 9, 13	
Iron	1, 4, 5, 7-12, 14-16	2, 3, 6	13 photometric (orthophenanthroline)
Tin	1-3, 5-9, 11, 13-15	10, 12	4, 16 photometric (phenylfluorone)
Cobalt	1, 2, 4-7, 10-13, 15, 16	3, 8, 9, 14	
Nickel	2-5, 8-13	1, 7	6 volumetric (DMGO/EDTA)
Copper	1, 2, 5, 7-13	3, 4, 6, 14	
Bismuth	2-5, 7-9, 11-13	1, 6	10 photometric (Brucine)
Antimony	1, 2, 4, 7-13	3, 5, 6	
Arsenic	1, 4-6, 8-12	2, 3, 7	
Chromium	1-5		
Manganese	1-6		

## Notes

This Certified Reference Material has been produced and certified, wherever possible, in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2000 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with this method of casting have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face, to a depth of ~15mm. Material to the rear of the disc, to a depth of ~5mm, is not certified.

There is a possibility for microstructural changes within this sample due to recrystallisation; and diffusion effects may lead to the concentration of some elements at the surface. For X-ray and other superficial sampling techniques, it is therefore recommended that the surface is refreshed immediately prior to use. In all other respects, this sample will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture.

All production records will be retained for a period of 20 years from the date of original analysis. Technical support for this certification will therefore expire in October 2033, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.