

# CERTIFICATE OF ANALYSIS

## 41X GLV4 (batch C)

### Certified Reference Material Information

Type: ZINC GALVANIZING ALLOY (CAST)  
Form and Size: Disc 50mm Diameter x 20mm Thickness  
Produced by: J Watson  
Certified and supplied by: MBH Analytical Ltd

### Assigned Values

#### Percentage element by weight

Element	Pb	Al	Cd	Fe	Sn	Cu	Ni
Value <sup>1</sup>	0.0062	0.514	0.0006	0.0028	0.0024	0.0321	0.0441
Uncertainty <sup>2</sup>	0.0003	0.006	0.0001	0.0003	0.0003	0.0009	0.0015

Element	Cr	Mn	Mg	Bi	Sb	Co	As
Value <sup>1</sup>	0.0007	0.0089	0.0034	0.0061	0.0287	0.0037	(0.0003)
Uncertainty <sup>2</sup>	0.0001	0.0005	0.0001	0.0003	0.0013	0.0003	-

Note: values given in parentheses are not certified - they are provided for information only.

### Definitions

- <sup>1</sup> The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- <sup>2</sup> The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

### Certified by:

MBH ANALYTICAL LIMITED \_\_\_\_\_

on 30<sup>th</sup> May 2008

C Eveleigh



## **Method of Preparation**

This reference material was produced from commercial-purity zinc, with the traces added as pure elements. The metal was cast from the bulk melt by sequential transfer of aliquots into individual iron chill moulds. At least 1mm has been machined from the working face of each disc, to minimise surface effects.

## **Sampling**

Samples for chemical analysis were taken from throughout the casting process. In addition, at least 10% of all discs, chosen at random from the complete cast, were checked for homogeneity.

## **Homogeneity**

The discs were checked for sample and batch uniformity using an optical emission spectrometer. One disc was checked for vertical uniformity using the same method.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

## **Chemical Analysis**

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2000, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

## **Estimation of Uncertainties**

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ( $C_{(95\%)}$ ) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

## **Traceability**

Most of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to a national authority. It is part of the requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised primary reference materials.

## **Usage**

Intended use:	With optical emission and X-ray fluorescence spectrometers.
Recommended method of use:	Zinc and zinc alloys are generally prepared by machining on a mill or lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.  Preparation should be the same for reference materials and the samples for test.  For OES the sample should be of sufficient mass to prevent excess heating during sparking, and the discharge chamber should be regularly cleaned as directed by the instrument manufacturer.  A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

## Analytical Data

### Percentage element by weight

Sample	Pb	Al	Cd	Fe	Sn	Cu	Ni
1	0.0054	0.497	0.0005	0.0022	0.0015	0.0300	0.0385
2	0.0057	0.501	0.0005	0.0022	0.0017	0.0302	0.0406
3	0.0058	0.506	0.0005	0.0025	0.0020	0.0304	0.0428
4	0.0060	0.507	0.0006	0.0025	0.0020	0.0310	0.0432
5	0.0061	0.512	0.0006	0.0027	0.0023	0.0312	0.0440
6	0.0062	0.515	0.0006	0.0028	0.0023	0.0315	0.0440
7	0.0062	0.518	0.0006	0.0030	0.0023	0.0320	0.0442
8	0.0064	0.518	0.0006	0.0030	0.0025	0.0323	0.0446
9	0.0064	0.519	0.0006	0.0032	0.0025	0.0323	0.0455
10	0.0067	0.522	0.0007	0.0032	0.0027	0.0325	0.0458
11	0.0067	0.525	0.0008	0.0037	0.0030	0.0330	0.0464
12	0.0072	0.529	0.0010		0.0031	0.0333	0.0467
13					0.0035	0.0348	0.0470
14						0.0348	
<b>Mean</b>	<b>0.0062</b>	<b>0.514</b>	<b>0.0006</b>	<b>0.0028</b>	<b>0.0024</b>	<b>0.0321</b>	<b>0.0441</b>
<b>Std Dev</b>	0.0005	0.010	0.0001	0.0005	0.0006	0.0015	0.0024
<b>C<sub>(95%)</sub></b>	0.0003	0.006	0.0001	0.0003	0.0003	0.0009	0.0015

Sample	Cr	Mn	Mg	Bi	Sb	Co	As
1	0.0005	0.0081	0.0032	0.0053	0.0251	0.0030	0.0002
2	0.0005	0.0082	0.0033	0.0054	0.0254	0.0032	0.0002
3	0.0005	0.0083	0.0033	0.0056	0.0265	0.0033	0.0004
4	0.0006	0.0084	0.0033	0.0056	0.0266	0.0033	<0.0005
5	0.0007	0.0087	0.0033	0.0061	0.0282	0.0035	<0.0005
6	0.0007	0.0089	0.0034	0.0062	0.0294	0.0036	<0.0005
7	0.0007	0.0090	0.0035	0.0062	0.0297	0.0036	<0.0005
8	0.0008	0.0095	0.0035	0.0062	0.0300	0.0036	<0.001
9	0.0011	0.0100	0.0035	0.0063	0.0300	0.0039	<0.001
10		0.0102	0.0035	0.0063	0.0304	0.0040	<0.001
11			0.0036	0.0064	0.0304	0.0040	
12			0.0037	0.0065	0.0306	0.0043	
13				0.0070	0.0314	0.0044	
<b>Mean</b>	<b>0.0007</b>	<b>0.0089</b>	<b>0.0034</b>	<b>0.0061</b>	<b>0.0287</b>	<b>0.0037</b>	<b>(0.0003)</b>
<b>Std Dev</b>	0.0002	0.0007	0.0001	0.0005	0.0021	0.0004	-
<b>C<sub>(95%)</sub></b>	0.0001	0.0005	0.0001	0.0003	0.0013	0.0003	-

Note: C<sub>(95%)</sub> is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

## Participating Laboratories

Bodycote Materials Testing	Middlesbrough, England	UKAS accreditation 0239
Sheffield Assay Office	Sheffield, England	UKAS accreditation 0012
Universal Scientific Laboratory Pty Ltd	Milperra, NSW, Australia	NATA accreditation 492
Laboratory Testing, Inc	Hatfield, PA, USA	A2LA accreditation 0117
Genitest Inc	Montreal, Canada	PRI accreditation 123077
Luo Yang Copper	Luo Yang, He Nan, China	CNAL accreditation 0173
Institute of Iron & Steel Technology	Shanghai, China	CNAL accreditation 0783
Laboratory TUV-Nord	Brno, Czech Republic	CAI accreditation 1060
TCR Engineering Services Ltd	Mumbai, India	NABL accreditation 0367
Sargam Metals Pvt Ltd	Chennai, India	NABL accreditation 0025
Institute of Non-Ferrous Metals	Gliwice, Poland	PCA accreditation AB274
De Bruyn Spectroscopic Solutions Ltd	Johannesburg, South Africa	
Rotech Laboratories Ltd	Wednesbury, England	

Note: to achieve National Accreditation (eg UKAS, NATA, A2LA, PRI, CNAL, CAI, NABL, PCA), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

## Analytical Methods Used

ELEMENT	RESULT No. & METHOD			
	ICP-AES	ICP-MS	FAAS	OTHER
Lead	3-5, 7, 9-12	-	1, 2, 6, 8	
Aluminium	1-5, 8, 9, 12	-	10, 11	6, 7 photometric (chrome azurol S)
Cadmium	1-3, 7-11	6	4, 5, 12	
Iron	2-5, 7-9, 11	6	1, 10	
Tin	2-8, 10-12	9	1	
Copper	1, 3, 4, 7-14	-	2, 5, 6	
Nickel	1, 2, 4, 6, 7, 9-13	-	3, 5, 8	
Chromium	2-4, 6-8	1	5, 9	
Manganese	2-4, 7, 8, 10	-	1, 5, 6, 9	
Magnesium	3-6, 8-12	1	2, 7	
Bismuth	1-4, 7, 8, 11-13	9	5, 6, 10	
Antimony	3, 4, 6, 8-13	-	1, 2, 5, 7	
Cobalt	1, 3, 5, 7-11, 13	2	4, 6, 12	
Arsenic	5-10	4	1	2, 3 photometric (molybdenum blue)

## Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2000, ISO Guide 31-2000 and ISO Guide 35-1989, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with this method of casting have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face of the disc, to a depth of 15mm. Material to the rear of the disc, to a depth of ~5mm, is not certified.

This material will remain stable provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of original analysis. This certification will therefore expire in May 2028, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.