

CERTIFICATE OF ANALYSIS

43X Z14 (batch E)

Certified Reference Material Information

Type: ZINC / ALUMINIUM / COPPER (CAST)
Form and Size: Disc 50mm Diameter x 20mm Thickness
Produced by: J Watson
Certified and supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

Element	Pb	Mg	Al	Cd	Fe	Sn	Cu
Value ¹	0.015	0.0133	8.05	0.0083	0.031	0.0054	1.13
Uncertainty ²	0.002	0.0006	0.07	0.0002	0.003	0.0003	0.02

Element	Ni	Mn	Cr	Ti	Si	Sb	Bi
Value ¹	0.0066	0.0050	0.0047	0.0014	0.016	0.0089	0.0096
Uncertainty ²	0.0004	0.0004	0.0003	0.0002	0.002	0.0005	0.0006

Definitions

- ¹ The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- ² The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:

MBH ANALYTICAL LIMITED _____

on 28th May 2008

C Eveleigh



Method of Preparation

This reference material was produced from commercial-purity zinc, with the majors and traces added as master alloys or pure elements. The metal was cast from the bulk melt by sequential transfer of aliquots into individual iron moulds. At least 1mm has been machined from the working face of each disc, to minimise surface effects.

Sampling

Samples for chemical analysis were taken from throughout the casting process. In addition, at least 10% of all discs, chosen at random from the complete cast, were checked for homogeneity.

Homogeneity

The discs were checked for sample and batch uniformity using an optical emission spectrometer. One disc was checked for vertical uniformity using the same method.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2000, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Most of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to a national authority. It is part of the requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised primary reference materials.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Zinc and zinc alloys are generally prepared by machining on a mill or lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

For OES the sample should be of sufficient mass to prevent excess heating during sparking, and the discharge chamber should be regularly cleaned as directed by the instrument manufacturer.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

Sample	Pb	Mg	Al	Cd	Fe	Sn	Cu
1	0.0112	0.0120	7.912	0.0076	0.0235	0.0045	1.072
2	0.0123	0.0122	8.000	0.0077	0.0255	0.0046	1.085
3	0.0148	0.0125	8.013	0.0081	0.0279	0.0050	1.110
4	0.0152	0.0127	8.025	0.0082	0.0289	0.0050	1.12
5	0.0154	0.0131	8.033	0.0082	0.0290	0.0052	1.121
6	0.016	0.0132	8.036	0.0083	0.0295	0.0053	1.122
7	0.0169	0.0134	8.05	0.0083	0.0304	0.0053	1.126
8	0.0170	0.0134	8.083	0.0083	0.0307	0.0054	1.126
9	0.0182	0.0135	8.094	0.0085	0.0345	0.0055	1.141
10		0.0139	8.102	0.0085	0.0346	0.0057	1.147
11		0.014	8.106	0.0087	0.0364	0.0060	1.161
12		0.0154	8.11	0.0087	0.0378	0.0062	1.176
Mean	0.0152	0.0133	8.047	0.0083	0.031	0.0054	1.126
Std Dev	0.0022	0.0009	0.058	0.0003	0.004	0.0005	0.029
C_(95%)	0.0017	0.0006	0.037	0.0002	0.003	0.0003	0.018

Sample	Ni	Mn	Cr	Ti	Si	Sb	Bi
1	0.0051	0.0043	0.0040	0.0008	0.0120	0.0078	0.0081
2	0.0060	0.0045	0.0042	0.0010	0.0125	0.0080	0.0089
3	0.0063	0.0045	0.0043	0.0010	0.0156	0.0081	0.0090
4	0.0064	0.0046	0.0044	0.0013	0.016	0.0082	0.0091
5	0.0064	0.0047	0.0045	0.0014	0.0160	0.0082	0.0092
6	0.0066	0.0047	0.0046	0.0014	0.0160	0.0087	0.0092
7	0.0069	0.0049	0.0047	0.0014	0.0160	0.0087	0.0093
8	0.0070	0.0052	0.0048	0.0015	0.0184	0.0091	0.0093
9	0.0070	0.0054	0.0048	0.0015	0.0187	0.0093	0.0094
10	0.0072	0.0055	0.0050	0.0015	0.0191	0.0093	0.0100
11	0.0075	0.0058	0.0053	0.0016	0.0203	0.0098	0.0100
12		0.0061	0.0053	0.0017		0.0099	0.0113
13			0.0056	0.0018		0.0100	0.0122
Mean	0.0066	0.0050	0.0047	0.0014	0.0164	0.0089	0.0096
Std Dev	0.0007	0.0006	0.0005	0.0003	0.0026	0.0008	0.0011
C_(95%)	0.0004	0.0004	0.0003	0.0002	0.0017	0.0005	0.0006

Note: C_(95%) is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Bodycote Materials Testing Sheffield Assay Office Universal Scientific Laboratory Pty Ltd Laboratory Testing, Inc Genitest Inc Luo Yang Copper Institute of Iron & Steel Technology Laboratory TUV-Nord TCR Engineering Services Ltd Sargam Metals Pvt Ltd Institute of Non-Ferrous Metals De Bruyn Spectroscopic Solutions Ltd Rotech Laboratories Ltd	Middlesbrough, England Sheffield, England Milperra, NSW, Australia Hatfield, PA, USA Montreal, Canada Luo Yang, He Nan, China Shanghai, China Brno, Czech Republic Mumbai, India Chennai, India Gliwice, Poland Johannesburg, South Africa Wednesbury, England	UKAS accreditation 0239 UKAS accreditation 0012 NATA accreditation 492 A2LA accreditation 0117 PRI accreditation 123077 CNAL accreditation 0173 CNAL accreditation 0783 CAI accreditation 1060 NABL accreditation 0367 NABL accreditation 0025 PCA accreditation AB274
---	--	--

Note: to achieve National Accreditation (eg UKAS, NATA, A2LA, PRI, CNAL, CAI, NABL, PCA), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT	RESULT No. & METHOD		
	ICP-AES	FAAS	OTHER
Lead	1, 4, 6, 7, 9	2, 3, 5, 8	
Magnesium	1, 3, 5, 7-11	2, 4, 6, 12	
Aluminium	1, 3, 6, 7, 9, 10, 11	4, 5	12 volumetric (EDTA) 2, 8 photometric (chrome azurol-S)
Cadmium	1, 2, 6, 8-12	3, 4, 5, 7	
Iron	4-9, 11, 12	1, 2, 10	3 photometric (orthophenanthroline)
Tin	2, 4-12	1	3 ICP-MS
Copper	1-3, 5-8, 10, 12	4, 9, 11	
Nickel	1, 2, 5, 7-11	3, 4, 6	
Manganese	2-4, 7-12	1, 5, 6	
Chromium	2, 3, 5-11, 13	4, 12	1 ICP-MS
Titanium	4, 6-13	1	2, 5 photometric (diantipyryl methane) 3 ICP-MS
Silicon	1-3, 7, 9, 10		4, 5, 8 photometric (molybdenum blue) 6, 11 gravimetric (perchloric acid)
Antimony	1, 4-7, 9, 10, 12, 13	3, 8, 11	2 ICP-MS
Bismuth	1, 3-5, 7-9, 11, 12	2, 10, 13	6 ICP-MS

Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2000, ISO Guide 31-2000 and ISO Guide 35-1989, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with this method of casting have led to the formation of inhomogeneous segregates in the rear portion of the disc. However, testing has shown that the above certification is applicable from the front face of the disc to a depth of 14mm. Material to the rear of the disc, to a depth of ~6mm, is not certified.

This material will remain stable provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of original analysis. This certification will therefore expire in May 2028, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.