

# CERTIFICATE OF ANALYSIS

**511X G05H2 (batch H)**

## Certified Reference Material Information

Type: ALUMINIUM / MAGNESIUM (CAST)  
Form and Size: Disc ~50mm diameter  
Produced by: MBH Analytical Ltd  
Certified and Supplied by: MBH Analytical Ltd

## Assigned Values

### Percentage element by weight

Element	Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn
Value <sup>1</sup>	0.188	3.58	0.299	0.641	0.124	0.157	0.372	0.049	0.0495
Uncertainty <sup>2</sup>	0.002	0.04	0.007	0.007	0.002	0.003	0.005	0.002	0.0012

Element	Ti	Cr	V	Zr	Cd	Be	B	Hg
Value <sup>1</sup>	0.068	0.172	0.0248	0.0105	0.0023	0.0018	0.0083	0.0031
Uncertainty <sup>2</sup>	0.002	0.003	0.0006	0.0005	0.0001	0.0001	0.0004	0.0004

## Definitions

- <sup>1</sup> The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- <sup>2</sup> The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

## Certified by:

MBH ANALYTICAL LIMITED \_\_\_\_\_

on 15th April 2015

C Eveleigh



## **Method of Preparation**

This reference material was produced from commercial-purity aluminium. The main alloys and trace elements were added as commercial hardeners and master alloys. The melt was degassed using sodium-free flux, prior to casting by sequential transfer of aliquots into individual iron moulds. Approximately 2mm has been removed from the cast face of each disc, to minimise any surface effects.

## **Sampling**

Samples for chemical analysis were taken from various positions throughout the batch. Approximately 10% of all discs were selected for non-destructive homogeneity testing.

## **Homogeneity**

The discs were checked for sample and batch uniformity using an optical emission spectrometer.

Using the combined data for each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

## **Chemical Analysis**

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials. The individual values listed overpage are the average of each analyst's results.

## **Estimation of Uncertainties**

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ( $C_{(95\%)}$ ) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

## **Traceability**

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

## **Usage**

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Aluminium alloys are generally prepared by machining on a mill or a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

## Analytical Data

### Percentage element by weight

Sample	Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn
1	0.182	3.488	0.283	0.631	0.120	0.148	0.365	0.0451	0.0469
2	0.184	3.497	0.285	0.631	0.120	0.149	0.365	0.0453	0.0475
3	0.185	3.500	0.292	0.632	0.121	0.152	0.365	0.0460	0.0482
4	0.185	3.518	0.293	0.636	0.122	0.154	0.366	0.0460	0.0483
5	0.186	3.523	0.298	0.638	0.123	0.154	0.367	0.0486	0.0493
6	0.186	3.531	0.301	0.638	0.123	0.155	0.370	0.0486	0.0494
7	0.187	3.582	0.301	0.644	0.123	0.155	0.371	0.0489	0.0498
8	0.188	3.602	0.306	0.646	0.124	0.156	0.376	0.0490	0.0503
9	0.191	3.605	0.311	0.647	0.125	0.156	0.376	0.0491	0.0506
10	0.192	3.627	0.311	0.648	0.126	0.160	0.382	0.0491	0.0507
11	0.193	3.638	0.313	0.650	0.126	0.161	0.385	0.0499	0.0512
12	0.193	3.660		0.651	0.126	0.163		0.0502	0.0523
13	0.193	3.664			0.128	0.164		0.0511	
14		3.708			0.129	0.164		0.0521	
15					0.131	0.164		0.0525	
<b>Mean</b>	<b>0.188</b>	<b>3.582</b>	<b>0.299</b>	<b>0.641</b>	<b>0.124</b>	<b>0.157</b>	<b>0.372</b>	<b>0.0488</b>	<b>0.0495</b>
<b>Std Dev</b>	0.004	0.072	0.010	0.008	0.003	0.005	0.007	0.0023	0.0016
<b>C<sub>(95%)</sub></b>	0.002	0.042	0.007	0.005	0.002	0.003	0.005	0.0013	0.0010

Sample	Ti	Cr	V	Zr	Cd	Be	B	Hg
1	0.0631	0.168	0.0233	0.0091	0.0020	0.0015	0.0075	0.0024
2	0.0647	0.169	0.0234	0.0092	0.0021	0.0015	0.0077	0.0026
3	0.0653	0.169	0.0238	0.0099	0.0021	0.0016	0.0078	0.0027
4	0.0654	0.170	0.0238	0.0100	0.0021	0.0016	0.0081	0.0030
5	0.0659	0.171	0.0241	0.0104	0.0022	0.0018	0.0085	0.0032
6	0.0662	0.171	0.0244	0.0106	0.0023	0.0018	0.0085	0.0033
7	0.0677	0.171	0.0245	0.0108	0.0023	0.0018	0.0086	0.0036
8	0.0685	0.171	0.0250	0.0109	0.0024	0.0018	0.0088	0.0038
9	0.0695	0.172	0.0252	0.0109	0.0024	0.0018	0.0092	
10	0.0698	0.173	0.0252	0.0110	0.0025	0.0020		
11	0.0703	0.175	0.0253	0.0110	0.0025	0.0020		
12	0.0713	0.176	0.0258	0.0112	0.0025	0.0020		
13	0.0724	0.178	0.0258	0.0115	0.0026	0.0021		
14			0.0259					
15			0.0266					
<b>Mean</b>	<b>0.0677</b>	<b>0.172</b>	<b>0.0248</b>	<b>0.0105</b>	<b>0.0023</b>	<b>0.0018</b>	<b>0.0083</b>	<b>0.0031</b>
<b>Std Dev</b>	0.0028	0.003	0.0010	0.0007	0.0002	0.0002	0.0006	0.0005
<b>C<sub>(95%)</sub></b>	0.0017	0.002	0.0006	0.0005	0.0001	0.0001	0.0004	0.0004

Note: C<sub>(95%)</sub> is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

## Participating Laboratories

Exova Ltd	Middlesbrough, England	UKAS accreditation 0239
Sheffield Assay Office	Sheffield, England	UKAS accreditation 0012
Birmingham Assay Office	Birmingham, England	UKAS accreditation 0667
Universal Scientific Laboratory Pty	Milperra, NSW, Australia	NATA accreditation 0492
Genitest Inc	Montreal, Canada	PRI accreditation 123077
Shanghai Jinyi Test Technology Co	Shanghai, China	CNAL accreditation 0783
South-West Aluminium Group	Jiulong Puo, Sichuan, China	CNAL accreditation T007
Bureau Veritas CPS Pvt Ltd	Chennai, India	NABL accreditation 0025
TCR Engineering Servs Pvt Ltd	Mumbai, India	NABL accreditation T367
Raghavendra SpectroMet Laboratory	Bangalore, India	NABL accreditation T371
Institute of Non-Ferrous Metals	Gliwice, Poland	PCA accreditation AB274
Tec-Eurolab	Campogalliano, Italy	ACCREDIA accreditation 52
London & Scandinavian Met. Co	Rotherham, England	
Colehill Laboratories Ltd	Birmingham, England	
Lithea sro	Brno, Czech Republic	

Note: to achieve the above accreditation (eg UKAS, NATA, etc), test houses are required to demonstrate conformity to the general requirements of EN ISO/IEC 17025.

## Analytical Methods Used

ELEMENT	RESULT No. & METHOD		
	ICP-AES	FAAS	OTHER
Copper	1, 3, 6-12	2, 4, 5, 13	
Magnesium	1, 2, 4-7, 9, 10, 13, 14	3, 11, 12	8 volumetric (EDTA)
Silicon	1-3, 6, 10, 11	-	4, 8 photometric (molybdenum blue)
Iron	1-3, 5, 7, 8, 10-12	6, 9	5, 7, 9 gravimetric (perchloric acid)
Manganese	5-15	2-4	4 photometric (orthophenanthroline)
Nickel	1-5, 7-12	6, 13-15	1 photometric (periodate)
Zinc	2, 3, 5-9	1, 4, 10, 11	
Lead	1, 3, 4, 7-10, 12-15	2, 5, 6, 11	
Tin	3-10, 12	1, 2	11 photometric (phenylfluorone)
Titanium	1, 2, 4, 7-13	6	3 photometric (di-antipyryl methane)
Chromium	1-4, 6-11	5, 12, 13	5 ICP-MS
Vanadium	1-3, 5-7, 9-11, 13-15	4, 8	12 photometric (5 Br-PADAP)
Zirconium	1-5, 7, 9-13	-	6 ICP-MS
Cadmium	1, 2, 4, 6-11, 13	2, 3, 5, 12	8 photometric (thiocyanate)
Beryllium	2-4, 7-13	1, 5	6 photometric (SCR)
Boron	1-9	-	
Mercury	1, 3-8	-	2 CV-AAS

## Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2000 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with semi-chill casting of this alloy, have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face of the disc for a depth of 8mm. Material to the rear of the disc, to a depth of ~7mm, is not certified.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of original analysis. Technical support for this certification will therefore expire in April 2035, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The specification, preparation, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.