

# CERTIFICATE OF ANALYSIS

**56X G2000J2 (batch C)**

## Certified Reference Material Information

Type: ALUMINIUM / COPPER (CAST)  
Form and Size: Disc 50mm diameter x 20mm thick  
Produced by: Coleshill Laboratories Ltd  
Certified and Supplied by: MBH Analytical Ltd

## Assigned Values

### Percentage element by weight

Element	Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Co
Value <sup>1</sup>	3.73	1.292	0.517	1.38	0.837	0.149	0.711	1.114	0.056
Uncertainty <sup>2</sup>	0.04	0.013	0.004	0.02	0.008	0.003	0.012	0.014	0.002

Element	Sn	Ti	Cr	Zr	Bi	V	Ag	Be	Li
Value <sup>1</sup>	0.092	0.096	0.0200	0.188	0.078	0.170	0.0446	0.0054	0.0112
Uncertainty <sup>2</sup>	0.002	0.003	0.0009	0.003	0.003	0.006	0.0013	0.0003	0.0008

## Definitions

- <sup>1</sup> The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- <sup>2</sup> The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

## Certified by:

MBH ANALYTICAL LIMITED \_\_\_\_\_ on 6<sup>th</sup> April 2010

C Eveleigh



## **Method of Preparation**

This reference material was produced from commercial-purity aluminium. The main alloys and trace elements were added as pure elements or master alloys. The melt was cast by sequential transfer of aliquots into individual iron moulds. Approximately 2mm has been removed from the cast face of each disc, to minimise any surface effects.

## **Sampling**

Samples for chemical analysis were taken from various positions throughout the batch. Approximately 10% of all discs were selected for non-destructive homogeneity testing.

## **Homogeneity**

The discs were checked for sample and batch uniformity using an optical emission spectrometer.

Using the combined data for each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

## **Chemical Analysis**

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials. The individual values listed overpage are the average of each analyst's results.

## **Estimation of Uncertainties**

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ( $C_{(95\%)}$ ) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

## **Traceability**

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

## **Usage**

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Aluminium alloys are generally prepared by machining on a mill or a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

## Analytical Data

### Percentage element by weight

Sample	Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Co
1	3.651	1.251	0.508	1.338	0.817	0.141	0.690	1.076	0.0533
2	3.676	1.274	0.510	1.374	0.825	0.143	0.690	1.086	0.0546
3	3.701	1.283	0.513	1.375	0.826	0.144	0.701	1.098	0.0556
4	3.712	1.284	0.516	1.376	0.828	0.147	0.706	1.112	0.0557
5	3.712	1.286	0.516	1.388	0.831	0.147	0.707	1.113	0.0558
6	3.726	1.288	0.517	1.393	0.835	0.148	0.709	1.115	0.0563
7	3.733	1.295	0.522	1.397	0.837	0.150	0.712	1.120	0.0563
8	3.738	1.308	0.522		0.838	0.151	0.722	1.121	0.0566
9	3.755	1.312	0.522		0.843	0.151	0.726	1.123	0.0568
10	3.770	1.313	0.522		0.850	0.152	0.729	1.140	0.0571
11	3.772	1.314	0.524		0.858	0.152	0.729	1.148	0.0580
12	3.781				0.859	0.157			
13	3.810								
<b>Mean</b>	<b>3.73</b>	<b>1.292</b>	<b>0.517</b>	<b>1.377</b>	<b>0.837</b>	<b>0.149</b>	<b>0.711</b>	<b>1.114</b>	<b>0.0560</b>
<b>Std Dev</b>	0.04	0.019	0.005	0.020	0.013	0.005	0.014	0.021	0.0013
<b>C<sub>(95%)</sub></b>	0.03	0.013	0.004	0.018	0.008	0.003	0.010	0.014	0.0008

Sample	Sn	Ti	Cr	Zr	Bi	V	Ag	Be	Li
1	0.0889	0.0935	0.0179	0.183	0.0750	0.161	0.0423	0.0048	0.0093
2	0.0897	0.0944	0.0187	0.184	0.0753	0.163	0.0431	0.0049	0.0102
3	0.0905	0.0951	0.0190	0.187	0.0755	0.165	0.0432	0.0053	0.0105
4	0.0913	0.0953	0.0200	0.188	0.0756	0.167	0.0446	0.0053	0.0108
5	0.0922	0.0961	0.0200	0.188	0.0777	0.168	0.0452	0.0054	0.0110
6	0.0925	0.0966	0.0204	0.188	0.0780	0.171	0.0455	0.0055	0.0115
7	0.0928	0.0969	0.0204	0.189	0.0786	0.173	0.0455	0.0056	0.0116
8	0.0928	0.0972	0.0205	0.191	0.0788	0.174	0.0471	0.0056	0.0116
9	0.0931	0.0977	0.0212	0.195	0.0793	0.174		0.0059	0.0117
10		0.0985	0.0223		0.0803	0.175		0.0059	0.0137
11		0.0988			0.0806	0.178			
<b>Mean</b>	<b>0.0915</b>	<b>0.0964</b>	<b>0.0200</b>	<b>0.188</b>	<b>0.0777</b>	<b>0.170</b>	<b>0.0446</b>	<b>0.0054</b>	<b>0.0112</b>
<b>Std Dev</b>	0.0015	0.0017	0.0013	0.004	0.0021	0.005	0.0016	0.0004	0.0012
<b>C<sub>(95%)</sub></b>	0.0012	0.0011	0.0009	0.003	0.0014	0.004	0.0013	0.0003	0.0008

Note: C<sub>(95%)</sub> is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

## Participating Laboratories

Exova Materials Testing Ltd  
Sheffield Assay Office  
Universal Scientific Laboratory Pty  
Genitest Inc  
Institute of Iron & Steel Technology  
Luo Yang Copper Co  
South-West Aluminium Group  
Sargam Metals Pvt Ltd  
TCR Engineering Servs Pvt Ltd  
Raghavendra SpectroMet Laboratory  
De Bruyn Spectroscopic Solutions  
London & Scandinavian Met. Co  
Coleshill Laboratories Ltd

Middlesbrough, England  
Sheffield, England  
Milperra, NSW, Australia  
Montreal, Canada  
Shanghai, China  
Luo Yang, He Nan, China  
Jiulong Puo, Sichuan, China  
Chennai, India  
Mumbai, India  
Bangalore, India  
Johannesburg, South Africa  
Rotherham, England  
Birmingham, England

UKAS accreditation 0239  
UKAS accreditation 0012  
NATA accreditation 0492  
PRI accreditation 123077  
CNAL accreditation 0783  
CNAL accreditation 0173  
CNAL accreditation T007  
NABL accreditation T025  
NABL accreditation T367  
NABL accreditation T371

Note: to achieve the above accreditation (eg UKAS, NATA, etc), test houses are required to demonstrate conformity to the general requirements of EN ISO/IEC 17025.

## Analytical Methods Used

ELEMENT	RESULT No. & METHOD		
	ICP-AES	FAAS	OTHER
Copper	1-4, 8, 9, 11, 13	5-7, 10, 12	
Magnesium	1, 3, 4, 8-11	2, 5-7	
Silicon	1, 9-11	-	5, 6, 8 2-4, 7
Iron	5-7	1	2-4
Manganese	1, 2, 4, 5, 7-10, 12	3, 6-8	11
Nickel	1, 2, 4-6, 11, 12	3, 7-10	
Zinc	1, 2, 4, 5, 9-11	3, 6-8	
Lead	1, 2, 4, 5, 8, 10	3, 6, 7, 9, 11	
Cobalt	1, 3, 6-9, 11	2, 4, 5, 10	
Tin	2-4, 7, 9	1, 5	6, 8
Titanium	2, 6-10	4, 5	1, 3, 11
Chromium	1, 2, 4, 7, 9, 10	3, 5, 6, 8	
Zirconium	1-5, 8, 9	-	6 7
Bismuth	1, 5-8, 11	3, 4, 9, 10	2
Vanadium	1, 2, 5, 7-9, 11	3, 4, 10	6
Silver	1, 5, 8	2-4, 6, 7	
Beryllium	2-4, 9, 10	1, 5, 7, 8	6
Lithium	3, 4, 6, 8-10	1, 2, 7	5

## Notes

This Certified Reference Material has been produced and certified in accordance with the requirements of ISO Guide 34-2000, ISO Guide 31-2000 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with semi-chill casting of this alloy, have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face of the disc for a depth of 12mm. Material to the rear of the disc, to a depth of ~8mm, is not certified.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of original analysis. This certification will therefore expire in April 2030, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The specification, preparation, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.