

83X PR8 D Page 1 of 4 December 2015

HOLLAND HOUSE • QUEENS ROAD • BARNET • EN5 4DJ • ENGLAND • TEL: +44 (0)20 8441 2024 • FAX: +44 (0)20 8449 0810 email: info@mbh.co.uk web: www.mbh.co.uk

CERTIFICATE OF ANALYSIS

83X PR8 (batch D)

Certified Reference Material Information

Type: LEAD WITH IMPURITIES (CAST)

Form and Size: Disc ~40mm diameter

Produced by: MBH Analytical Ltd

Certified and supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

Element	Sn	Sb	Bi	Cu	Cd	Ag	Au
Value ¹	0.604	0.257	1.18	0.0448	0.199	0.497	0.0106
Uncertainty ²	0.009	0.006	0.02	0.0007	0.003	0.005	0.0004

Element	As	ln	Ni	Se	Te	Zn	Hg
Value ¹	0.134	0.293	0.0008	(0.0003)	0.0014	0.0004	0.086
Uncertainty ²	0.004	0.008	0.0001	-	0.0003	0.0001	0.003

Note: values given in parentheses are not certified - they are provided for information only.

Definitions

- The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

(<u>Certified</u>	by	/:

on 16th December 2015

MBH ANALYTICAL LIMITED ______ C Eveleigh

Method of Preparation

This reference material was produced from commercial-purity lead; the trace elements were added as single elements or as binary alloys. The melt was cast by sequential transfer of aliquots into iron moulds. 2mm has been removed from the working face to minimise any surface effects.

Sampling

Samples for chemical analysis were taken from various positions throughout the casting process. Approximately 10% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

The discs were checked for sample and batch uniformity using an optical emission spectrometer.

Using the combined data for each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025 - 2005, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials. In addition, some of the results derived as part of this testing programme have traceability to NIST standards, as part of the analytical calibration or process control.

<u>Usage</u>

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use:

Lead and its alloys are generally prepared by machining on a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

1 0.5903 0.2450 1.133 0.0432 0.1920 0.4872 0.0094 2 0.5911 0.2507 1.139 0.0432 0.1935 0.4937 0.0105 3 0.5986 0.2509 1.142 0.0433 0.1939 0.4940 0.0105 4 0.5990 0.2517 1.157 0.0442 0.1940 0.4950 0.0106 5 0.6090 0.2544 1.159 0.0446 0.1980 0.4955 0.0106 6 0.6090 0.2544 1.171 0.0448 0.1984 0.4958 0.0106 6 0.6090 0.2544 1.171 0.0448 0.1984 0.4958 0.0106 7 0.6092 0.2590 1.185 0.0449 0.2000 0.4972 0.0108 8 0.6101 0.2593 1.189 0.0451 0.2002 0.4982 0.0109 9 0.6130 0.2660 1.202 0.0452 0.2017 0.4990 0.5016	Sample	Sn	Sb	Bi	Cu	Cd	Ag	Au
3 0.5986 0.2509 1.142 0.0433 0.1939 0.4940 0.0105 4 0.5990 0.2517 1.157 0.0442 0.1940 0.4950 0.0106 5 0.6090 0.2540 1.159 0.0446 0.1980 0.4955 0.0106 6 0.6090 0.2544 1.171 0.0448 0.1984 0.4958 0.0107 7 0.6092 0.2590 1.185 0.0449 0.2000 0.4972 0.0108 8 0.6101 0.2593 1.189 0.0451 0.2002 0.4982 0.0109 9 0.6130 0.2660 1.202 0.0452 0.2017 0.4990 0.0112 10 0.6130 0.2680 1.213 0.0453 0.2020 0.5016 0.0112 12 1.232 0.0458 0.2036 0.5070 1.232 0.0463 0.2051 14 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0006	1	0.5903	0.2450	1.133	0.0432	0.1920	0.4872	0.0094
4 0.5990 0.2517 1.157 0.0442 0.1940 0.4950 0.0106 5 0.6090 0.2540 1.159 0.0446 0.1980 0.4955 0.0106 6 0.6090 0.2544 1.171 0.0448 0.1984 0.4958 0.0107 7 0.6092 0.2590 1.185 0.0449 0.2000 0.4972 0.0108 8 0.6101 0.2593 1.189 0.0451 0.2002 0.4982 0.0109 9 0.6130 0.2660 1.202 0.0452 0.2017 0.4990 0.0110 10 0.6130 0.2680 1.213 0.0453 0.2020 0.5016 0.0112 11 0.2724 1.220 0.0455 0.2020 0.5070 0.5070 12 1.232 0.0458 0.2036 0.5070 0.0461 0.2051 14 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C _(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 <th></th> <th></th> <th>0.2507</th> <th></th> <th></th> <th></th> <th>0.4937</th> <th></th>			0.2507				0.4937	
5 0.6090 0.2540 1.159 0.0446 0.1980 0.4955 0.0106 6 0.6090 0.2544 1.171 0.0448 0.1984 0.4958 0.0107 7 0.6092 0.2590 1.185 0.0449 0.2000 0.4972 0.0108 8 0.6101 0.2593 1.189 0.0451 0.2002 0.4982 0.0109 9 0.6130 0.2660 1.202 0.0452 0.2017 0.4990 0.0110 10 0.6130 0.2680 1.213 0.0453 0.2020 0.5016 0.0112 11 0.2724 1.220 0.0455 0.2020 0.5070 0.5070 12 1.232 0.0458 0.2036 0.2051 0.0463 Mean 0.6042 0.2574 1.179 0.0448 0.1988 0.4967 0.0106 Std Dev 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C _(95%) 0.0062								
6 0.6090 0.2544 1.171 0.0448 0.1984 0.4958 0.0107 7 0.6092 0.2590 1.185 0.0449 0.2000 0.4972 0.0108 8 0.6101 0.2593 1.189 0.0451 0.2002 0.4982 0.0109 9 0.6130 0.2660 1.202 0.0452 0.2017 0.4990 0.0110 10 0.6130 0.2680 1.213 0.0453 0.2020 0.5016 0.0112 11 0.2724 1.220 0.0455 0.2020 0.5070 0.0112 12 1.232 0.0458 0.2036 0.2051 0.0463 0.0461 0.2051 0.04663 Mean 0.6042 0.2574 1.179 0.0448 0.1988 0.4967 0.0106 Std Dev 0.0087 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 C _(95%) 0.0062 0.0057 0.021 0.00020 0.0006 0.00015								
7 0.6092 0.2590 1.185 0.0449 0.2000 0.4972 0.0108 8 0.6101 0.2593 1.189 0.0451 0.2002 0.4982 0.0109 9 0.6130 0.2660 1.202 0.0452 0.2017 0.4990 0.0110 10 0.6130 0.2680 1.213 0.0453 0.2020 0.5016 0.0112 11 0.2724 1.220 0.0455 0.2020 0.5070 0.5070 12 1.232 0.0458 0.2036 0.5070 0.0461 0.2051 13 0.0461 0.2051 0.0463 0.0463 0.0051 0.0066 Std Dev 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C _(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818								
8 0.6101 0.2593 1.189 0.0451 0.2002 0.4982 0.0109 9 0.6130 0.2660 1.202 0.0452 0.2017 0.4990 0.0110 10 0.6130 0.2680 1.213 0.0453 0.2020 0.5016 0.0112 11 0.2724 1.220 0.0455 0.2020 0.5070 0.5070 12 1.232 0.0458 0.2036 0.2051 0.5070 13 0.0461 0.2051 0.0463 0.0463 0.0463 Std Dev 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C _(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.00015 2 0.1310 0.2820 0.00057								
9 0.6130 0.2660 1.202 0.0452 0.2017 0.4990 0.0110 10 0.6130 0.2680 1.213 0.0453 0.2020 0.5016 0.0112 11 0.2724 1.220 0.0455 0.2020 0.5070 0.5070 12 1.232 0.0458 0.2036 0.2051 0.0461 0.2051 13 0.0463 0.0463 0.0463 0.0463 0.04663 0.04663 Std Dev 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C _(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0021 0.0828 2 0.1310 0.2820 0.00057 0.00022 0.0010 0.00023 0.0828 3								
10 0.6130 0.2680 1.213 0.0453 0.2020 0.5016 0.0112 11 0.2724 1.220 0.0455 0.2020 0.5070 12 12 1.232 0.0458 0.2036 0.2051 1.232 0.0461 0.2051 0.0463								
11 0.2724 1.220 0.0455 0.2020 0.5070 12 1.232 0.0458 0.2036 0.2051 13 0.0461 0.2051 0.2051 14 0.0463 0.0463 0.04663 Std Dev 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0787 2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829								
12 1.232 0.0458 0.2036 13 0.0461 0.2051 14 0.0463 0.0463 Mean 0.6042 0.2574 1.179 0.0448 0.1988 0.4967 0.0106 Std Dev 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C _(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0787 2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829		0.6130						0.0112
13 14 0.0461 0.0463 0.2051 0.0463 Mean 0.6042 0.2574 1.179 0.0448 0.1988 0.4967 0.0106 Std Dev 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C _(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0787 2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829			0.2724				0.5070	
14 0.0463 Mean 0.6042 0.2574 1.179 0.0448 0.1988 0.4967 0.0106 Std Dev 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C _(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0787 2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829				1.232				
Mean 0.6042 0.2574 1.179 0.0448 0.1988 0.4967 0.0106 Std Dev 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C _(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0787 2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829						0.2031		
Std Dev 0.0087 0.0084 0.033 0.0010 0.0043 0.0050 0.0005 C _(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0787 2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829	14				0.0400			
C _(95%) 0.0062 0.0057 0.021 0.0006 0.0026 0.0034 0.0003 Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0787 2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829	Mean	0.6042	0.2574	1.179	0.0448	0.1988	0.4967	0.0106
Sample As In Ni Se Te Zn Hg 1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0787 2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829	Std Dev	0.0087	0.0084	0.033	0.0010	0.0043	0.0050	0.0005
1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0787 2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829	C _(95%)	0.0062	0.0057	0.021	0.0006	0.0026	0.0034	0.0003
1 0.1272 0.2818 0.00055 0.00020 0.0006 0.00015 0.0787 2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829		-						
2 0.1310 0.2820 0.00057 0.00022 0.0008 0.00021 0.0828 3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829	Sample	As	ln	Ni	Se	Te	Zn	Hg
3 0.1319 0.2831 0.00070 0.00022 0.0010 0.00023 0.0829	1	0.1272	0.2818	0.00055	0.00020	0.0006	0.00015	0.0787
		0.1310	0.2820	0.00057	0.00022	0.0008	0.00021	0.0828
4 0.1330 0.2848 0.00070 0.00030 0.0013 0.00040 0.0852								
5 0.1336 0.2880 0.00077 0.00033 0.0014 0.00042 0.0864								
6 0.1340 0.2930 0.00080 0.00040 0.0015 0.00048 0.0867								
7 0.1351 0.2960 0.00080 0.00050 0.0015 0.00048 0.0868								
8 0.1387 0.2964 0.00080 <0.0005 0.0016 0.00050 0.0887					<0.0005			
9 0.1416 0.2966 0.00080 0.0017 0.00058 0.0895 10 0.3007 0.00087 0.0019 0.00060 0.0897		0.1416						
••								
••						0.0020	0.00000	0.0921
12 0.3009 0.00101 13 0.3082 0.00116								
Mean 0.1340 0.2933 0.00080 0.00031 0.0014 0.00042 0.0863		0.1340	0.2933	0.00080	0.00031	0.0014	0.00042	0.0863
Std Dev 0.0042 0.0086 0.00016 0.00011 0.0004 0.00016 0.0038	Std Dev	0.0042	0.0086	0.00016	0.00011	0.0004	0.00016	0.0038
C _(95%) 0.0032 0.0052 0.00010 0.00010 0.0003 0.00011 0.0026								

Note:

 $C_{(95\%)}$ is the 95% half-width confidence interval derived from the equation:

 $C_{(95\%)} = (t \times SD)/\sqrt{n}$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Sheffield Analytical Services
Anchorcert Analytical
Universal Scientific Laboratory Pty Ltd
Genitest, Inc
Shanghai Jinyi Test Tech Co
Luo Yang Copper
Bureau Veritas CPS Pvt Ltd
Raghavendra SpectroMet Laboratory
Institute of Non-Ferrous Metals
Tec-Eurolab
AMG Superalloys UK Ltd
Coleshill Laboratories Ltd
AIM Metals and Alloys LP
Laboratory Inppamet
Analyticka Laborator Lithea sro

Sheffield, England
Birmingham, England
Milperra, NSW, Australia
Montreal, Canada
Shanghai, China
Luo Yang, He Nan, China
Chennai, India
Bangalore, India
Gliwice, Poland
Campogalliano, Italy
Rotherham, England
Coleshill, England
Montreal, Canada
Calama, Chile
Brno, Czech Republic

UKAS accreditation 0012
UKAS accreditation 0667
NATA accreditation 0492
PRI accreditation 123077
CNAS accreditation L0041
CNAL accreditation 0173
NABL accreditation 0025
NABL accreditation T371
PCA accreditation AB274
ACCREDIA accreditation 52

Note: to achieve the above accreditation (eg UKAS, NATA, etc), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT			RESULT No. & M	ETHOD	
	ICP-AES	ICP-MS	FAAS		OTHER
Tin	1-3, 5-7	8	10	4 9	photometric (phenylfluorone) volumetric (iodide)
Antimony	1, 3, 5-8, 11	-	2, 4, 10	9	volumetric (bromate)
Bismuth	1, 3, 4, 6-10	-	2, 5, 12	11	photometric (iodide)
Copper	2, 3, 5, 6, 8-13	-	1, 4, 7, 14		
Cadmium	1, 2, 6, 8-10, 12, 13	-	3-5, 7, 11		
Silver	2, 4, 6-10	-	1, 3, 5, 11		
Gold	2-7, 9, 10	1	8		
Arsenic	1, 3, 5-8	9	2, 4		
Indium	1, 3-6, 8, 10-13	-	2, 7, 9		
Nickel	4, 6-12	3, 13	1, 2, 5		
Selenium	1, 3, 5, 7, 8	6	2, 4		
Tellurium	1-5, 7-11	-	6		
Zinc	1, 4, 5, 7, 8, 10	3, 11	2, 6, 9		
Mercury	1-5, 7-11	6	-		

Notes

This Certified Reference Material has been produced and certified, wherever possible, in accordance with the requirements of ISO Guide 34-2009, ISO Guide 31-2015 and ISO Guide 35-2006, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with this method of casting have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face of the disc, to a depth of 10mm. Material to the rear of the disc, to a depth of ~5mm, is not certified.

This material is liable to superficial corrosion. There is also a possibility for microstructural changes due to recrystallisation, and diffusion effects may lead to the concentration of some elements at the surface. For X-ray and other superficial sampling techniques, it is therefore recommended that the surface is refreshed immediately prior to use. In all other respects, this sample will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture.

All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in December 2015, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.